

July 28, 2011

REVISION OF SECTION 703  
CONCRETE AGGREGATES

**NOTICE**

This is a standard special provision that revises or modifies CDOT's *Standard Specifications for Road and Bridge Construction*. It has gone through a formal review and approval process and has been issued by CDOT's Project Development Branch with formal instructions for its use on CDOT construction projects. It is to be used as written without change. Do not use modified versions of this special provision on CDOT construction projects, and do not use this special provision on CDOT projects in a manner other than that specified in the instructions unless such use is first approved by CDOT's Standards and Specifications Unit. The instructions for use on CDOT construction projects appear below.

Other agencies which use the *Standard Specifications for Road and Bridge Construction* to administer construction projects may use this special provision as appropriate and at their own risk.

**Instructions for use on CDOT construction projects:**

Use on projects having any type of concrete construction.

July 28, 2011

REVISION OF SECTION 703  
CONCRETE AGGREGATES

Section 703 of the Standard Specifications is hereby revised for this project as follows:

Delete the second paragraph of subsection 703.00 and Table 703-1.

Delete subsections 703.01 and 703.02 and replace with the following:

**703.01 Fine Aggregate for Concrete.** Fine aggregate for concrete shall conform to the requirements of AASHTO M 6, Class A. The minimum sand equivalent, as tested in accordance with Colorado Procedure 37 shall be 80 unless otherwise specified. The fineness modulus, as determined by AASHTO T 27, shall not be less than 2.50 or greater than 3.50 unless otherwise approved.

**703.02 Coarse Aggregate for Concrete.** Coarse aggregate for concrete shall conform to the requirements of AASHTO M 80, Class A aggregates, except that the percentage of wear shall not exceed 45 when tested in accordance with AASHTO T 96.