SCOPE

This chapter intends to provide the CDOT Project Testers, Inspectors the Owner Acceptance Frequency Guide schedule for Materials Testing, Sampling, and Inspection from the beginning of a project to the closure of the project. The Materials Testing, Sampling and Inspection on a project needs to be accurate, complete, and processed in the project files. The materials documentation on a project needs to be accurate, complete, and processed in the project files. The materials documentation on a project needs to be accurate, complete, and processed within the officially established time frame after the issuance of the project's Final Acceptance Letter per Section 105.21 (b). The Department has stipulated that the Letter of Final Materials Certification (CDOT Form 473) will be signed by the indicated representatives within 30 calendar days to ensure that the quality of the project is maintained and to avoid legal and contractual conflicts.

LOCAL AGENCIES ARE TO USE AN AASHTO ACCREDITED LAB for the test procedures required, NOT CDOT Central Lab.

The following information and link to the CDOT Forms are for your reference and use.

- For SMM/LIMS Projects, report test results in the CDOT SMM/LIMS.
- For SMM/LIMS, Summary forms such as CDOT Form 6, 58, 69, 156, 212, 323 are no longer required.
- CDOT Forms 6, 58, 69, 82, 83, 84, 157, 212, 411, 554, 1304 are listed as CDOT Materials Forms-Serialized (2017 and newer) and can be located at: <u>https://www.codot.gov/library/forms</u>
- COCs and CTRs do not require a CDOT Form 157.
- Non-SMM/LIMS Projects, All CDOT forms will be completed as required.
- CDOT Form 43 and CDOT Form 1373 referenced are generated from the CAR reporting system.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	{New Forms designed to	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIE ACCREDITED LA	S ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
EMBANKMENT stained on ¾ Inch Sieve) 20	IN-PLACE DENSITY/ PERCENT RELATIVE COMPACTION	 1 per 1,000 cu yds or fraction thereof with one additional test per change in material type. DENSITY: 1 per 500 cu. yds. when within 100 ft. of Bridge Approach(s), with a minimum 1 test per lift, and 1 additional test per change in material type. 1 per soil type with additional tests required per change in the material 		CP 80 CP 25 CP 23* T 99 or T 180	<i>CP</i> 25 for 1-point check requirements A minimum of 1/5000 cu. yds. Use CDOT Form 427. Report on CDOT Forms 212. Use CDOT Form 427, to include where roller hours only are specified. See FMM (Chapter 200) for further details. *When more than 5% oversize is present., run CP 23 Rock Correction. Report on CDOT Form 24. Test using T99 or T180 depending on	In the compacted lift. From un-compacted lift or stockpile.		
EMBANKM ≤ 30% Retained on	CURVE	type being placed.		T 85*	soil classification. *If oversize is present a sufficient sample is needed to run a T85			
(≤ 30%	SOIL CLASSIFICATION	1 per soil type		M 145	Use AASHTO M 145 for soil classification. Report on CDOT Form 564.	From un-compacted lift or stockpile.		
	GRADATION	1 per soil type		CP 21	Report on CDOT Form 564	From un-compacted lift or stockpile.		
	ATTERBERG LIMITS	1 per soil type		T 89 T 90	Report on CDOT Form 564	From un-compacted lift or stockpile.		

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {New Forms designed to	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIES ACCREDITED LAE	ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
203	TEST STRIP CONSTRUCTION AND ACCEPTANCE	1 per test strip constructed. 1 test strip is required per material type.			Observation and acceptance of roller pattern, moisture conditioning, and proof rolling.	In the compacted test strip.		
lnch Sieve), .L	SOIL CLASSIFICATION	1 per soil type.		M145	Use AASHTO M 145 for Soil Classification. Report on CDOT Form 219.	From un-compacted lift or stockpile.		
Retained on % Ir and ROCK FILL	GRADATION	1 per soil type.		CP 21		From un-compacted lift or stockpile.		
ith > 30% NKMENT	ATTERBERG LIMITS	1 per soil type.		T 89 T 90		From un-compacted lift or stockpile.		
SOIL EMBANKMENT (with > 30% ROCK EMBANKMENT	SLAKE DURABILITY	1 per stockpile / borrow source and 1 per material type for sedimentary rock only.		CPL 3104		From un-compacted lift or stockpile.		

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCEDURES		REMARKS	{New Forms designed to follow SMM Templates.}	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIES ACCREDITED LAB	ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	FOR QUALITY DETERMINATION		TEST FREQUENCY	SAMPLE SIZE	
11, ROCK FILL	SOIL-SURVEY (CLASSIFICATION)	1 per 1,000 lin. ft. of a two-lane roadway or fraction thereof.	CP 20 CP 24	CP 21 M 145 T 89 T 90 T 190	Use AASHTO <i>M 145 for soil classification.</i> Report on CDOT Form 219.	In the top 2 ft. (600 mm) of the finished subgrade.	Soil-Survey shall be performed on the soil found at the proposed profile grade in the Field Lab or the Region Lab. 1 - R-value test, per general soil type. (Per T 190)	33 lb. (15 kg) (minus) #4 If the criteria are met for CP 24, Section 4.1, use CDOT Form 564 to classify the material.	
BANKMEN	WATER-SOLUBLE SULFATE ION * / **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source of imported material.	CP 30	CPL 2103	Report on CDOT Form 212. Use CDOT Form 323. Results for Chemical Tests, use CAR report - Soils Report	From un-compacted lift or stockpile.	1 water-soluble sulfate, water- soluble chloride, resistivity, and	5 lb. (3 kg) per soil type. (minus)#4 material.	
ROCK EM	WATER-SOLUBLE CHLORIDE ION **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source of imported material.	CP 30	CPL 2104	See Chapter 200, Soil Survey / Preliminary Soil Profile. * Sulfate test required for fill	,	pH test per source. (See NOTE 1)		
SOIL EMBANKMENT, ROCK EMBANKMENT, ROCK FILL	RESISTIVITY **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source of imported material.	CP 30	G 57	around concrete structures. ** For pipe backfill these tests may be required based on the pipe material type. See Subsection 203.03.				
ALL SOIL	рН **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source of imported material.	CP 30	G 51					

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {New Forms designed to	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIES ACCREDITED LAI	S ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
2000	CLASS 1						1 per source,	440 lb (45 km)
206	GRADATION	1 per 200 cu. yds. Or fraction thereof.	CP 30	CP 31	Report on CDOT Form 6. Use CDOT Form 565.	In-Place, before compaction.	per project. (See NOTE 1)	110 lb. (45 kg) is approx. 2 bags by volume
	ATTERBERG LIMITS	1 per 200 cu. yds. Or fraction thereof.	CP 30	T 89 T 90			1 per source, per project. (See NOTE 1)	for Class 1, 55 lb. (25 kg)
	CLASS 2 GRADATION	If in the roadbed, 1 per source, or soil type.	CP 30	CP 21	Use CDOT Forms 564.			for Class 2. See Chap. 300.
	ATTERBERG LIMITS	If in the roadbed, 1 per source, or soil type.	CP 30	M 145 T 89 T 90				
. BACKFILL CLASS 2)	IN-PLACE DENSITY / PERCENT RELATIVE COMPACTION	1 per 200 cu. yds. Or fraction thereof. Minimum 1 per structure.	CP 30	CP 80	Report on CDOT Form 6. Use CDOT Form 427. See FMM, Chap. 200, Item 206 Structure Backfill. Note: When more than 5% oversize is present, run CP23 Rock Correction	In the compacted lift.		
STRUCTURAL (CLASS 1 & (CP 25	<i>CP 25</i> for 1-point check requirements A minimum of 1/5000 cu. yds. Use CDOT Form 427.			
STR (C	MOISTURE DENSITY CURVE	If in the roadbed, 1 per source or soil type.	CP 30	CP 23 T 99 <u>or</u> T 180	Report on CDOT Form 24. Class 1: T 180 Class 2: T 99 or T 180, depending on soil type.		1 per source, per project. (See NOTE 1)	
	WATER-SOLUBLE SULFATE ION * / **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	CPL 2103	Report on CDOT Form 212. Use CDOT Form 323.	From un-compacted lift or stockpile.	Minimum of 1 per source for	5 lb. (3 kg) per soil type. (minus) #4
	WATER-SOLUBLE CHLORIDE ION **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	CPL 2104	See Chapter 200, Soil Survey / Preliminary Soil Profile.		CP-L 2103, CP- L 2104, G51, and G57. (See NOTE 1)	(minus) #4 material.
	RESISTIVITY **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	G 57	 * Sulfate test required for fill around concrete structures. ** For pipe backfill these tests may be required based on the pipe 			
	pH **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	G 51	material type. See Subsection 206.02 (a).			

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

PAY	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {New Forms designed to	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIE ACCREDITED LA	S ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
206	GRADATION	1 per 200 cu. yds. Or fraction thereof.	CP 30	CP 31	Report on CDOT Form 6. Use CDOT Form 564 or 565.	In-Place.	1 per source, per project. (See NOTE 1)	55 lb. (25 kg)
TERIAL	ATTERBERG LIMITS	1 per 200 cu. yds. Or fraction thereof.		T 89 T 90			1 per source, per project. (See NOTE 1)	
COURSE MATERIAL	WATER-SOLUBLE SULFATE ION * / **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	CPL 2103	Report on CDOT Form 212. Use CDOT Form 323. See Chapter 200, Soil Survey / Preliminary Soil Profile. * Sulfate test required for fill around concrete structures.	se CDOT Form 323. ee Chapter 200, Soil Survey / reliminary Soil Profile. Sulfate test required for fill round concrete structures. For pipe backfill these tests hay be required based on the ipe material type.		5 lb. (3 kg) per soil type. (minus) #4
D COUF	WATER-SOLUBLE CHLORIDE ION **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	CPL 2104				material.
BED	RESISTIVITY **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	G 57	** For pipe backfill these tests may be required based on the pipe material type. See Subsection 206.02 (a).			
	рН **	1 per 2,000 cu yds. Or fraction thereof. Minimum 1 per source.	CP 30	G 51	See Subsection 200.02 (a).			
FILTER 0 MATERIAL 9	GRADATION	1 per 200 cu. yds. Or fraction thereof for each Class.	CP 30	CP 31	Report on CDOT Form 6. See FMM, Chapter 200 for further details. Use CDOT Form 564 or 565.	In-Place.	1 per source, per project. (See NOTE 1)	55 lb. (25 kg) is approx. 1 full bag by volume.

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available

206	Submit to project files a Flow-Fill mix design that documents adherence to the Specifications.
FILL FLOW	
207	Topsoil (Onsite): Visual-inspect on-site topsoil to determine compliance with specifications or contract documents. Locations of on-site topsoil shall be discussed in the Site Pre-vegetation Conference (Contract requirement 207.03). (See Note 1)
	Seeding Media: Acceptance Method: <u>CTR</u> The Contractor shall provide the Engineer a <u>Certified Test Report</u> documenting: pH, Salts by Electrical Conductivity, SAR, Rock Content, Trace Contaminants, Rock Content, Texture, Particle Size, Physical Contaminants, and C: N Ratio as specified in the Contract Documents. All tests shall be performed by an independent laboratory participating in the National Association for Proficiency Testing (NAPT).
TOPSOIL	 Topsoil (Offsite): Acceptance Method: both <u>CTR</u> and <u>COC</u> The Contractor shall provide the Engineer a <u>Certified Test Report</u> documenting: pH, Salts by Electrical Conductivity, SAR, OM, N-P-K, Rock Content, Bioassay, Texture, Physical Contaminants, Partial Sizes and C: N requirements as specified in the Contract Documents. All tests shall be performed by an independent laboratory participating in the National Association for Proficiency Testing (NAPT). The Contractor shall also provide the Engineer a <u>Certificate of Compliance (furnished by the supplier</u>) documenting that the source/location of the imported topsoil has controlled noxious weeds in accordance with the State of Colorado Noxious Weed Act. Field-inspect and documents that the material is acceptable, then retain all copies in the Project Files.
101	Topsoil (Wetland): Visual-inspect on-site wetland topsoil to determine compliance with specifications or contract documents. Locations of on-site wetland topsoil shall be shown on the plans or as directed. (See Note 2)
	Subgrade Soil Preparation: Visual-inspect contractor testing to verity subsoil de-compaction to determine compliance with specifications or contract documents.
	Note 1 For Topsoil (Onsite) discussions from the Site Pre-vegetation Conference use the guidance from the Permanent Stabilization Subject Matter Expert as designated on the project's Stormwater Management Plan (SWMP).
	Note 2 For Topsoil (Wetland) use guidance from the Regional Wetland Biologist.
	INCIDENTAL ITEMS (Non-pay)
	Rod Penetrometer: Field-inspect and document that material meets the requirements of the contract, retain all copies in the Project Files.

208	Silt Dike: Acceptance Method: <u>COC</u> . Dimensions of silt dike including fabric extensions shall be measured as shown in Subsections 208.02 (i), staples shall be measured for gauge and length as indicated in Subsections 208.02 (i). <u>A Certificate of Compliance (furnished by the manufacturer)</u> is required indicating that geotextile meets the physical requirements shown in Subsection 208.02 (j) and as tested by ASTM D 4491, ASTM D 4623, and ASTM D 4595. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
EROSION CONTROL	 Erosion Log: Acceptance Method: <u>COC</u>. Erosion logs, Type 1, Type 2 shall be measured for minimum dimensions and weight as shown in the Revision of 208, Subsection 208.02 (j). Stakes shall be measured to meet nominal dimensions in Subsection 208.02 (h). Type 1: Excelsior logs shall be inspected to be fungus-free, resin-free, and free of growth or germination inhibiting substances. Type 2: The compost in (compost) logs shall be inspected per Subsection 212. Type 3: Excelsior logs shall be inspected to be fungus-free, resin-free, and free of growth or germination inhibiting substances. <u>A Certificate of Compliance (furnished by the manufacture)</u> is required indicating that netting consist of a 100% natural compostable fiber meets the physical requirements shown in Subsection 208.02 (i) and as tested by ASTM D 3822, and ASTM D 5988. Field-inspect. COC's do not require a CDOT From 157. Silt Berm: Acceptance Method: <u>Pre-Approved (with Contractor's AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl Silt berms shall be inspected and measured for the dimensions, including percent open area, as shown in Subsection 208.02 (e). Spikes shall be measured to be 10 to 12 inches by 0.375-inch diameter (minimum). Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files. Erosion Bales: Acceptance Method: <u>COC</u>. Erosion Bales: Acceptance Method: <u>COC</u>. Erosion Bales: Acceptance Method: Accepted the bales. A Certificate of Compliance is required showing the transit certificate number or a copy of the transit certificate as supplied by the forage producer.
	Bales shall be measured and weighed to have approximately 5 cubic feet of material (approximately 18 inches square and 36 inches long) and weigh at least 35 pounds. Wood stakes shall be measured to be 2 inches by 2 inches (nominal) and 30 inches long. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	 Silt Fence: Acceptance Method: <u>COC</u>. Posts must be measured to be 42 inches (min.) in length and 1.5 inches by 1.5 inches nominal. Posts shall be inspected to confirm that geotextile is attached to posts with 3 or more staples. A <u>Certificate of Compliance (furnished by the manufacturer)</u> is required indicating that geotextile meets the physical requirements shown in Subsection 208.02 (b) and as tested by ASTM D 4632, ASTM D 4491, and ASTM D 4355. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	(Continues on next Page)

	(Continued)
208	Aggregate bags: Acceptance Method: COC & CTR.
	Aggregate bags. Acceptance Method. <u>COC & CTR</u> . A <u>Certificate of Compliance</u> (Furnished by the Manufacturer) is required stating that the geotextile meets the property requirements of the Subsection 208.02 (n) as tested by ASTM D 4632, ASTM D 4533, ASTM D 3786, and ASTM D 4355.
	Aggregate bags shall be measured and weighed according to the Subsection 208.02 (m). Rubber in bags shall be inspected to be 95 percent free of metal and other particulates.
	A Certified Test Report is required to verify that the crushed stone contained in the aggregate bags shall conform to Subsection 703.09, Table 703-10 Gradation Specifications for Filter Material.
	Field-inspect that the material is acceptable, then retain all copies in the Project Files. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
CONTROL	Concrete Washout Structure: Acceptance Method: <u>COC</u> Dimensions of Concrete Washout Structure including impermeable synthetic liner extents shall be measured as shown on plans. When required a <u>Certificate of</u> <u>Compliance (furnished by the manufacturer)</u> is required indicating that impermeable synthetic liner meets the physical requirements shown in Subsection 208.02 (k) and as tested by ASTM D 5199, ASTM D 1004, and ASTM D 1790. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
EROSION CO	Prefabricated Concrete Washout Structure (Type 1 and 2): Acceptance Method: Pre-Approved (with Contractor's (APL Verification) for Documentation). <u>https://www.codot.gov/business/apl</u> Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files.
ERO	Storm Drain Inlet Protection (Type I, II, and III): Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). <u>https://www.codot.gov/business/apl</u>
	Vehicle Tracking Pad: Acceptance Method: <u>COC & CTR</u> . Aggregate shall be a minimum of two fractured faces and that it meets the gradation requirements of 208.02 (m). <u>CTR</u> Geotextile (Erosion Control) shall be Class 2 and conform to the requirements of Subsection 420.02. <u>COC</u> Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Prefabricated Vehicle Tracking Control: Acceptance Method: Pre-Approved (with Contractor's <u>APL Verification</u> for Documentation). <u>https://www.codot.gov/business/apl</u> Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

209 Water (Landscaping): Acceptance Method: <u>COC</u> or <u>CTR</u>.

WATERING

Contractor to provide document stipulating the source of the water if potable, Certified Test Report required if non-potable. Refer to Standard Specifications Subsection 209.02.

Dust Palliative (Magnesium Chloride): Acceptance Method: COC.

The Contractor shall provide one copy of a Certificate of Compliance. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

Embankment Moisture (water) Control: Acceptance Method: N/A

Sampling is not required unless chemical content and quality are in doubt. Refer to Standard Specifications Subsection 209.02. If water quality test results are required, follow instructions for Landscaping Water above. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

	Organic Fertilizer: Acceptance Method: COC.
212	Organic Fertilizer shall be inspected on-site and reviewed according to the Revision of Section 212, Subsection 212.02 (b) and have a Nitrogen chemical
	analysis as shown on the Stormwater Management Plan.
	Fertilizer which has become wet, moldy, or damaged in anyway including arriving on-site in unsealed bags or missing nutrient analysis label will not be
	accepted.
	Compost (Mechanically Applied): Acceptance Method: CTR.
	Compost shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (c):
	The contractor shall provide the Project Engineer a Certified Test Report (furnished by the compost facility) confirming the compost physical properties, and
	that the compost will be supplied from a producer that participates in the United States Composting Council's (USCC) Seal of Testing Assurance (STA)
	program. The Department will only accept STA-approved compost that is tested per the USCC Test Methods for Examining of Composting and Compost
	(TMECC) manual. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
	Biotic Soil Amendments (Hydraulically Applied): Acceptance Method: Pre-Approved (with Contractor's (APL Verification) for Documentation).
G	
Ž	https://www.codot.gov/business/apl
	Biotic Soil Amendments material packaging damaged in anyway including arriving on-site in unsealed bags or missing manufacturers label will not be accepted.
SEEDING, FERTILIZER, SOIL CONDITIONER, AND SODDING	Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files.
N N	Humate: Acceptance Method: COC
岂공	Humate shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (e), and field visual-inspect the humate to confirm that it
22	is a screened product with less than 2% fines. Packaging damaged in anyway including arriving on-site in unsealed bags or missing manufacturers label will not
	be accepted.
ΰÖ	
ΞĒ	Mycorrhizae: Acceptance Method: <u>COC, (CTR laboratory analysis for Acute Toxicity is no longer a requirement)</u> Mycorrhizae shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (f), Packaging damaged in anyway including arriving
	on-site in unsealed containers or missing manufacturers label will not be accepted.
ШQ	
" U	Elemental Sulfur: Acceptance Method: COC
J	Elemental Sulfur shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (g).
õ	
	Sod: Acceptance Method: COC.
	Sod shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (h). For each load of sod, the Contractor shall provide the Engineer a <u>Certificate Of Compliance</u> (furnished by the grower) confirming the sod type and date/time of field cutting.
	The Contractor shall submit to the Engineer a sample of sod two feet wide by five feet long, for a comparison standard. Compliance with Standard
	Specifications Subsection 212.02. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
	INCIDENTAL ITEMS (Non-pay)
	Seed (Either Native, Wetland, or Temporary): Acceptance Method: COC
	The Seed shall be inspected and reviewed according to the Revision of Section 212, Subsection 212.02 (a):
	Seed used on the project shall not be in the Contractor's possession for more than 30 days from the date of pickup or delivery as documented on the seed
	vendors packing slip.
	The Contractor shall provide the Engineer a <u>Certificate of Compliance (furnished by the CDA registered seed supplier)</u> certifying that the seed is from a lot
	that has been tested by a recognized laboratory for seed testing within 13 months before the date of seeding. The Engineer may obtain seed samples from the seeding equipment, furnished bags, or containers to test seed for species identification, purity, and
	germination. Seed tested and found to be less than 10 percent of the labeled certified PLS and different than the specified species will not be accepted.
	The Seed which has become wet, moldy, or damaged in anyway including arriving on-site in unsealed bags or missing seed label will not be accepted.
	Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
•	

213 MULCHING	 Mulching (Weed Free Hay or Straw): Acceptance Method: COC The contractor shall provide the Project a <u>Certificate of Compliance (furnished by the grower)</u> stating that the material is certified under the Colorado Department of Agriculture Weed Free Forage Certification Program. Each certified weed-free mulch bale shall consist of blue and orange twine, or the bale shall consist of blue and orange twine, or the bale shall consist of blue and accepted the Begional Forage Certification Program Number. The Contractor shall not unload certified weed-free mulch bales or remove their identifying twine, wire, or tags until the project has inspected and accepted the bales. The Contractor shall provide a transit certificate that has been filled out and signed by the grower and by the Department of Agriculture inspector. Straw or hay shall be inspected, and any found to be in a stage of decomposition (discolored, brittle, rotten, or moldy) or old, dry mulch which breaks in the crimping process will not be accepted. Field-inspect that the material is acceptable, then retain all copies in the Project Files. Colorado Department of Agriculture Weed Free Forage Directory website Mulching (Wood Chips): Acceptance Method: <u>COC</u> The Contractor shall provide the Engineer a <u>Certificate of Compliance (furnished by the supplier)</u> stating a description of the material and the approximate dimensions of the material is acceptable, then retain all copies in the Project Files Mulch Tackifier: Acceptance Method: <u>COC</u> Mulch Tackifier shall be inspected and reviewed according to Section 213, Subsection 213.02 (c). Packaging damaged in anyway including arriving on-site in unsealed bags or missing manufacturers label will not be accepted. Field-inspect that the material is acceptable, then retain all copies in the Project Files Mulch Tackifier shall be inspected and reviewe
	Spray on Mulch Blanket: Acceptance Method: COC The Contractor shall provide the Engineer a <u>Certificate of Compliance (furnished by the manufacturer</u>) stating that the product meets the property requirements shown Subsection 213.02. Field inspection is required for all mulching to evaluate installation for uniform cover and correct application rate per Section 213. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
	Bonded Fiber Matrix: Acceptance Method: <u>COC</u> The Contractor shall provide the Engineer a <u>Certificate of Compliance (furnished by the manufacturer)</u> stating that the product meets the property requirements shown in 213 Subsection 213.02. Field inspection is required for all mulching to evaluate installation for uniform cover and correct application rate per 213. Field-inspect that the material is acceptable, then retain all copies in the Project Files.

214	Nursery Stock: Acceptance Method: <u>COC</u> . The Contractor shall provide the Engineer a <u>Certificate of Compliance (furnished by the nursery/grower</u>) stating availability of species and minimum sizes of the nursery stock as designated on the plans. Contractor shall also provide proof of deposit that nursery stock has been secured for the project. If species or size substations are requested by the Contractor follow the approval requirements for Subsection 214.02. Using the guidance from the Regional Environmental Staff (see Note #1) nursery stock is visually inspected at the four following times. Any rejected nursery stock shall be immediately removed from the project site. (1) At the nursery stock supplier's (nursery or grower) location during pre-delivery inspection. (2) On the project site at the time of delivery, prior to planting. (3) At the time of installation.
	(4) At the partial or final acceptance walkthroughs on the project site. Field-inspect the material to ensure that each species is identified by means of supplier's label affixed to the plant or nursery container. Retain documents in
	the Project Files.
	Live Willow Stakes: Acceptance Method: COC
PLANTING	The Contractor shall provide the Engineer a <u>Certificate of Compliance</u> stating detailed description of the proposed harvest locations including written approval from the landowner when applicable. Also include the work plan details including harvest timeframe, storage location, and anticipated installation timing. Using the guidance from the Regional Environmental Staff (see Note #1) Live Willow Stakes are visually inspected for minimum diameter, length, and harvesting techniques. Any rejected Live Willow Stakes shall be immediately removed from the project site. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
LA	Live Brush Mattress: Acceptance Method: <u>COC</u>
<u>د</u>	The Contractor shall provide the Engineer a <u>Certificate of Compliance</u> stating detailed description of the proposed harvest locations including written approval from the landowner when applicable. Also include the work plan details including harvest timeframe, storage location, and anticipated installation timing. Using the guidance from the Regional Environmental Staff (see Note #1) live willow unrooted cuttings are visually inspected for minimum diameter, length, and harvesting techniques. Any rejected live willow unrooted cuttings shall be immediately removed from the project site. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
	Live Brush Fascine:
	The Contractor shall provide the Engineer a <u>Certificate of Compliance</u> stating detailed description of the proposed harvest locations including written approval from the landowner when applicable. Also include the work plan details including harvest timeframe, storage location, and anticipated installation timing. Using the guidance from the Regional Environmental Staff (see Note #1) live willow unrooted cuttings are visually inspected for minimum diameter, length, harvesting techniques, and percentage of live younger wood. Any rejected live willow unrooted cuttings shall be immediately removed from the project site. Field-inspect that the material is acceptable, then retain all copies in the Project Files.
	Note 1: Region Environmental Staff can consist of the Environmental Project Manager, Permanent Stabilization Subject Matter Expert, and Wetland Biologist.

1	OA FREQUENCY GUIDE SCHEDULE FOR MINIMUM Materials resung, Sampling, and Inspection
214	INCIDENTAL ITEMS (Non-pay)
(Continued)	
	Organic Fertilizer: Acceptance Method: COC Follow instructions in Section 212.
ഠ	Compost: Acceptance Method: COC Follow instructions in Section 212.
Ž	
L L	Wood stakes: Acceptance Method COC Visually inspect for minimum requirements of wood or metal T-post.
PLANTING	
<u>م</u>	Deciduous Tree Wrapping Materials: Acceptance Method <u>COC</u> Visually inspect for minimum requirements.
	Flex Pipe Bark Protector: Acceptance Method COC Visually inspect for minimum requirements.
	Wood Mulch: Acceptance Method COC Visually inspect for minimum requirements.
·	
215	
	Removed as per the Greg Fischer CDOT Landscape Architect 04-25-2023.
ч N N	
NAN	
TRANS- PLANTING	
<u> </u>	
	Soil Retention Blanket (Photo and Biodegradable Class_): Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation).
216	Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files.
	https://www.codot.gov/business/apl
	Turf Reinforcement Mat (Class_): Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation).
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
	Field-inspect and document on the form that the material is acceptable, then retain all copies in the Project Files.
N	https://www.codot.gov/business/apl
SOIL RETENTION COVERING	Earth Anchors: Acceptance Method: <u>COC and CTR</u>
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
	The Contractor shall submit to the Engineer a Certificate Of Compliance (furnished by the manufacturer). And also a Certified Test Result (furnished by the
чõ	manufacturer) showing the test results for standard tensile testing (ASTM A1007-07) and testing that the anchor system can provide the minimum holding
C S	strength in accordance with Subsection 213.03(g). Field-inspect that the material is acceptable, then retain all copies in the Project Files.
õ	INCIDENTAL ITEMS (Non-pay)
	Staples: Acceptance Method: <u>COC</u>
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
	Staples are not listed on the CDOT APL and is considered a part of Soil Retention Coverings and Turf Reinforcement mat as an incidental item. Measure for dimensions as shown in Subsection 216.02 (c). Field-inspect that the material is acceptable, then retain all copies in the Project Files.
U	

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

HERBICIDE TREATMENT 212	Field-inspect that Files. For herbicide(s) n Management Plan INCIDENTAL ITE Commercial Pes	 Herbicides: Acceptance Method: Project-by-Project Approval only. (No Longer listed on the CDOT Approved Products List) Field-inspect that all herbicides are supplied to the project in labeled containers, and document that the material is acceptable, then retain all copies in the Project Files. For herbicide(s) not designated in the contract use the guidance from the Permanent Stabilization Subject Matter Expert as designated on the project's Stormwater Management Plan (SWMP). INCIDENTAL ITEMS (Non-pay) Commercial Pesticide Applicators License: The Contractor shall provide the Engineer a copy of the Colorado Department of Agriculture commercial pesticide applicators license, retain all copies in the Project Files. 											
PAY	TYPE OF TEST												
ITEM		SAMPLING & TESTING FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	 {New Forms designed to follow SMM Templates.} 	VERIFICATION FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE					
304	GRADATION	1 per 2,000 tons or 1 per 1,000 cu. yds. or fraction thereof on each Class.	CP 30	CP 31	Report on CDOT Form 6. Use CDOT Form 564 or 565.	Immediately after pugmill mixing or from windrow.	1 per source, per project. (See NOTE 1)	55 lb. (25 kg) for Gradation Only.					
	ATTERBERG LIMITS	1 per 2,000 tons or 1 per 1,000 cu. yds. or fraction thereof on each Class.		T 89 T 90			1 per source, per project. (See NOTE 1)	110 lb. (50 kg) is required for full testing (moisture density curve).					
AGGREGATE BASE COURSE	IN-PLACE DENSITY / PERCENT RELATIVE COMPACTION	1 per 2,000 tons or 1 per 1,000 cu. yds. or fraction thereof.		CP 80 *CP 25	Report on CDOT Form 6. Use CDOT Form 427. *CP 25 for 1-point check required as needed for material changes. A minimum of 1/5000 cu. yds. When more than 5% oversize is present, run CP23 Rock Correction.	In the compacted lift.		or 55 lbs. (25 kg) In addition to other test samples. Note: 304 Class 1, Submit 3 full bags by volume.					
AG BAS	MOISTURE- DENSITY CURVE	1 per class/per source		CP 23 T 180 **T85	Report on CDOT Form 24. **If oversize is present a sufficient sample is needed to run a T85		1 per source, per project. (See NOTE 1)	304 Class 2-7, Submit 5 full bags by volume.					
	LA ABRASION	1 per class/per source		Т 96	LA Abrasion required for Class 4,5,6,7		1 per source, per project. <u>(See NOTE 1)</u>	-					
	R-VALUE	1 per class/per source		T 190			1 R-value test per Class.						

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCE	DURES	REMARKS {New Forms designed to follow SMM Templates.}	POINT OF VERIFICATION FOR QUALITY	CENTRAL I [LOCAL AGENCIES ACCREDITED LAB,	ARE TO USE AN
		TREQUENT	PROJECT PRO VERIFICATION VERIFI SAMPLING TES			DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
306 SNINOI	IN-PLACE DENSITY / PERCENT RELATIVE COMPACTION	1 per 5,000 sq. yds. or fraction thereof. 1 per 2,500 sq. yds. or fraction thereof for each shoulder (when shoulders only are specified).		CP 80 / *CP 25	Report on CDOT Form 212. Use CDOT Form 427. *CP 25 for 1-point check required as needed for changes in Material. A minimum of 1/5000 cu. yds. When more than 5% oversize is present, run CP23 Rock Correction.	In the compacted lift.		
RECONDITIONING	MOISTURE- DENSITY CURVE	1 per soil type.		CP 23 T 99 T 180 **T85	Report on CDOT Form 24. **If oversize is present a sufficient sample is needed to run a T85		(See NOTE 1)	

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available.

(Continued on next page)

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCE	DURES	REMARKS {New Forms designed to follow SMM Templates.}	POINT OF VERIFICATION FOR QUALITY	CENTRAL [LOCAL AGENCIES ACCREDITED LAI	S ARE TO USE AN
		The gold of	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	ionow Smin Templates.}	DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
307	IN-PLACE DENSITY / PERCENT RELATIVE COMPACTION	1 per 5,000 sq. yds. Or fraction thereof; or as specified in the Contract.		CP 80 *CP 25	Report on CDOT Form 212. Use CDOT Form 427. *CP 25 for 1-point check required as needed for changes in Material. A minimum of 1/5000 cu. yds. When more than 5% oversize is present, run CP23 Rock Correction.	In the compacted lift.	The Region shall retain a Designated Agent Laboratory to perform the required tests if proper equipment is not available.	Process control test: Schedules for minimum sampling and testing conducted by the Contractor are listed in Standard Specification Section 307,
	GRADATION	1 per 5,000 sq. yds. Or fraction thereof.	CP 30	CP 31	1" – 100% passing #4 – 60% passing. Dry sieving after final mixing. Use CDOT Form 565.		No verification gradation samples are to be run in the field except for information only.	Table 307-1. Cost shall be included in the bid price.
	ATTERBERG LIMITS	1 per 5,000 sq. yds. Or fraction thereof.		T 89 T 90	Reduce by ½ original PI. As per Table 307-1 Use CDOT Form 565.		,	
) SUBGRADE	MOISTURE-DENSITY CURVE	1 per soil type.		CP 23 T 99 T 180	The moisture content of the mixture at the start of compaction shall be at 2 <u>+</u> 1% above optimum moisture content. *If oversize is present a sufficient		-	
ATED				*T85	sample is needed to run a T85 Report on CDOT Form 24.			
LIME TREATED	UNCONFINED COMPRESSIVE STRENGTH	1 per 5,000 sq. yds. Or fraction thereof.		D 5102 (Proc. B)	Tests shall be conducted on samples cured in a moist environment for 5 days @ 100 F.			
	THICKNESS ACCEPTANCE	1 per 1,500 sq. yds. Or fraction thereof.		C 174	When the measurement is <0.5", 2 additional cores shall be taken in that lot and the average of 3 cores will determine the thickness of that lot. As per Table 307-1.			
	SWELL TEST	1 per 5,000 sq. yds. Or fraction thereof.		D 4546 (Meth. B)	0.5% or less with 200 psf. surcharge pressure.	From the compacted roadway.		
	рН	1 per 5,000 sq. yds. Or fraction thereof.	CP 30	G 51	pH will be determined after % lime has been established based on unconfined compressive strength.			

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY		DURES	REMARKS {New Forms designed to follow SMM Templates.}	POINT OF VERIFICATION FOR QUALITY	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	Tonow Smin Templates.	DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
307 (Continued)	SULFATE	1 per soil type.		CPL 2103	Water-soluble sulfate content in soil shall be less than 0.2% by dry soil weight.		The Region shall retain a Designated Agent Laboratory to perform the	Process control test: Schedules for minimum sampling and testing conducted
LIME TREATED SUBGRADE	LIME GRADATION	1 per 100 tons of lime or fraction thereof, 1 per source, 1 per project.		CPL 4209	Retain one copy of the CTR along with the Form 157 for Project Files.		required tests if proper equipment is not available. No verification gradation samples are to be run in the field except for information only.	by the Contractor are listed in Standard Specification Section 307, Table 307-1. Cost shall be included in the bid price.

307	Hydrated Lime: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). (*) And <u>CTR</u> .
HYDRATED LIME For Soil Stabilization	https://www.codot.gov/business/apl The Contractor shall provide the Engineer with one copy of the Certified Test Report that is furnished by the supplier for Chemical Tests, per AASHTO M 303. Submit one copy of the CTR and send it to the Region Materials Engineer for review, comments, and approval. Obtain a 2 lb. sample according to AASHTO T 218 and submit it to the Central Laboratory for gradation verification testing. (CP-L 4209) before use. During Construction submit a 2 lb. sample, per 100 tons of lime or fraction thereof, (CP-L 4209). Minimum one per source/project. Provide Bill of Lading as per CP 11. Quicklime: Acceptance Method: <u>CTR</u> . Test results are to document the percent purity. No sample is required. (NOTE: number of tons of quicklime x 1.32 = tons of hydrated lime.) Provide the Bill of Lading per CP 11. * Document the lime source on CDOT Form 157, (include sufficient information on the CDOT Form 157 so that the supplier and source are easily identified)
MINERAL FILLERS	For project acceptance, test for gradation according to T 37 for Hydraulic Cement and CPL 4209 for Limestone Dust at 1 per 100 tons or fraction thereof used, and report on CDOT Form 6. Use CDOT Form 106 or 565. Submit a 2 lb. sample to Central Laboratory at a frequency of 1 per 500 tons or fraction thereof, for gradation check sample. The above frequency is only applicable when mineral fillers are required by the plans. Provide the Bill of Lading per CP 11.
FULL DEPTH RECLAMATION	Full Depth Reclamation: Established through a Project Special. Testing and sampling as specified in the contract. Density is performed at 1 per 4,000 square yards per 8-inch lift. As per CP 80 for testing. Use CDOT Form 427. Gradation per CP 31 is performed as required. Use CDOT Form 565.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROC	EDURES	REMARKS {New Forms designed to follow SMM Templates.}	POINT OF VERIFICATION FOR QUALITY	CENTRAL [LOCAL AGENCIES ACCREDITED LAR	S ARE TO USE AN
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	Similar Templates.	DETERMINATI	TEST FREQUENCY	SAMPLE SIZE
403	ASPHALT CONTENT	1 per 1,000 tons or fraction thereof of mix produced (or as specified in the contract). If less than 5,000 tons see special provisions.	CP 41 CP 55	CP 43 CP 85 CPL 5120	Mix Design as per CP 52; CDOT Form 43 required <u>before</u> the mix is produced. CAR Report - Asphalt Quality Level Report (AQL)	Plant discharge, at/or behind paver. For Central Lab Correction Factor, sample aggregate from belt and Binder from Contractors tank	CHECK TEST: Minimum of each 10k or fraction thereof. 1 sample (can) is submitted to Central Lab & one to the Region Lab.	50 lb. (23 kg)
LT (HMA): TANCE	AGGREGATE MOISTURE	Aggregate: 1 per 2,000 tons or fraction thereof of mix produced (or as specified in the contract).	CP 30	CP 33	Use CDOT Form 106, 107, or 565. Report results using Form 626 daily to the contractor and Project Engineer. Required 2% above absorption shown on the CDOT Form #43. See section 401.14 (2).	Aggregate from the cold feed.	Also needed for Central Lab Correction Factor when new 10K submitted. If Mix Design changes, submit Correction	25 lb. (Agg) 1 qt (binder)
HOT MIX ASPHALT (HMA): VOIDS ACCEPTANCE	GRADATION	Aggregate: 1 per 10,000 tons or fraction thereof of mix produced (or as specified in the contract).	CP 30	CP 31	CAR Report-Asphalt Quality Level Report (AQL)	Aggregate from the cold feed, pugmill discharge, extraction, or product of CP-L 5120.	Factor when next 10K is submitted. Submit Correction	100 lb. (45 kg) (Agg)
OH	MICRO DEVAL	1 per 10,000 tons as specified in the Contract.	CP 30	CPL 4211	Mix Design as per CP 52. CAR - Form 38 Physical Properties Aggregate Test Report.	Aggregate from the cold feed.		
	FRACTURED FACES AND VOID CONTENT FINE AGGREGATE	As requested by the RME.	CP 30	CP 45 T 304 A	Report on CDOT Form 58. CAR - Form 38 Physical Properties Aggregate Test Report.		403 Hot Mix Asphalt.	Note for all tests: 1 full bag of each aggregate type.
	IN-PLACE DENSITY	All lifts of Item 403: 1 per 500 tons (500 t) or fraction thereof of mix placed (or as specified in the contract). Minimum of 10 tests per project. If less than 5,000 tons see special provisions.		CP 44 CP 81 CP 82	CAR Report-Asphalt Quality Level Report (AQL). Use CDOT Form 428 or 582.	In the compacted lift.		If LA Abrasion is requested, send 1 additional full bag. Micro Deval cold feed is 1 full bag. 1 full bag is required to get the
	THERMAL SEGREGATION	As specified in the contract.		CP 58	Report on CDOT Form 1346.	Behind paver.		gradation needed to perform a "D"
	LONGITUDINAL JOINT DENSITY	1per 5,000 linear ft. of Joint Minimum of 5 tests per project.		CP 44	Report on CDOT Form 1290. Test template CP 44L in SMM.			Method.

PAY	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {New Forms designed	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIES ACCREDITED LAR	S ARE TO USE AN
	TEST	FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	to follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
403	THEORETICAL MAX. SP. GRAVITY	1 per 1,000 tons. Minimum of 1 test per day if less than 1 000 tons placed in a day.	CP 41 CP 55	CP 51 CP 56	Report on CDOT Form 69.	Plant discharge, at/or behind paver.	CHECK TEST: Minimum of each 10K or fraction thereof for:	50 lb. (23 kg)
	HVEEM STABILITY	1 per 10,000 tons.	CP 41 CP 55	CPL 5106	Report on Computer accept. form, or equivalent, or CDOT Form # 360 (see all test items).	Plant discharge, windrow, at/or behind paver.	Hveem Stability, Air Voids, and VMA. Central Lab will run the Lottman test on first 10K or as	
IMA): CE	AIR VOIDS	1 per 1,000 tons. Minimum of 5 tests per project. If less than 5,000 tons see special provisions.	CP 41 CP 55	CPL 5115		Plant discharge, windrow, at/or behind paver.	requested by the Region. See Guidelines for Test Frequency	
ASPHALT (HMA): ACCEPTANCE	VOIDS IN MINERAL AGGREGATE	1 per 1,000 tons. Minimum of 5 tests per project. If less than 5,000 tons see special provisions.	CP 41 CP 55	CP 48		Plant discharge, windrow, at/or behind paver.	Reduction Item 403 - Hot Mix Asphalt.	
IIX ASPI DS ACC	LOTTMAN	1 per 10,000 tons, or fraction thereof. (See Subsection 401.02)	CP 41 CP 55	CPL 5109 CPL 5115		Plant discharge, windrow, at/or behind paver.		
HOT MIX VOIDS	HAMBURG WHEEL- TRACKING	1 per project, or mix design change, or as requested by RME. (100 gyrations)	CP 41	CPL 5112	Submit sample to the Euro- Lab Unit of the Central Lab. Applicable with SuperPave	Plant discharge, windrow, at/or behind paver.	1 st 10K or each mix design change, or as requested by the	65 lb. (30 kg) for the Hamburg test
	FRENCH RUTTING- TESTER	1 per project, or mix design change, or as requested by RME. (100 gyrations)	CP 41	CPL 5114	gyratory compaction designs with 100 design revolutions <u>only</u> .		Region.	65 lb. (30 kg) for the French test.
	ASPHALT MIX PERFORMANCE TEST	As requested by RME. 1 st 10K or mix design change only.	CP 41	TBD	Submit sample to the Euro- Lab. Applicable with Super Pave gyratory compaction designs.		As requested by RME.	130 lb. (60 kg) for the AMPT.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS {New Forms designed to follow SMM Templates.}	{New Forms designed to VERIFICATION		CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING		DETERMINATION	TEST FREQUENCY	SAMPLE SIZE	
403	Ideal-CT	Submit for each project, 1 sample per mix design or 1 sample per 10,000 Tons.	TBD	TBD	Submit sample to the Euro- Lab Unit of the Central Lab. Applicable with SuperPave gyratory compaction.	Plant discharge, windrow, at/or behind paver.	Research	130 lb. (60 kg) 2-cans labeled. "Ideal-CT"	
HOT MIX ASPHALT (HMA): VOIDS ACCEPTANCE	PAVEMENT SMOOTHNESS	As specified in the contract. Within 14 days after completion of paving.		CP 74	Testing shall be performed by the Contractor and will be witnessed by the Engineer. Data will be transferred electronically and immediately transferred to the Engineer after testing. Data will be immediately transferred to the Central Lab for analysis.		The Central Lab will perform pavement smoothness verification testing. The min. testing will be statewide, once per certified profiler performing work and 25% of profiles submitted for a certified profiler.		

ΡΑΥ	TYPE OF TEST	PROJECT VERIFICATION	PROCE		REMARKS {New Forms designed to follow SMM	POINT OF VERIFICATION FOR QUALITY	CENTRAL [LOCAL AGENCIES ACCREDITED LAI	S ARE TO USE AN
ITEM		SAMPLING & TESTING FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	Templates.}	DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
403 :(WI	ASPHALT CONTENT	1 per 1,000 tons or fraction thereof of mix produced (or as specified in the contract).	CP 41 CP 55	CP 43 CP 85 CPL 5120	Mix Design as per CP 52; CDOT Form 43 required <u>before</u> the mix is produced. CAR Report - Asphalt Quality Level Report (AQL)	Plant discharge, at/or behind paver. For Central Lab Correction Factor, sample aggregate from belt and Binder from Contractors tank.	CHECK TEST: Minimum of each 10k or fraction thereof. 1sample (can) is submitted to Central Lab & one to the Region Lab.	50 lb. (23 kg)
STONE MATRIX ASPHALT (SMA) & HOT MIX ASPHALT (HMA): GRADATION ACCEPTANCE	AGGREGATE MOISTURE	Aggregate: 1 per 2,000 tons or fraction thereof of mix produced (or as specified in the contract).	CP 30	CP 33	Use CDOT Form 106, 107, or 565. Report results using Form 626 daily to the contractor and Project Engineer. Required 2% above absorption shown on the CDOT Form 43. See section 401.14 (2).	Aggregate from the cold feed.	Also needed for Central Lab Correction Factor when new 10K submitted. If Mix Design changes, submit Correction Factor when next 10K submitted. Submit Correction Factor at	25 lb. (Agg) 1 qt (binder)
ŝMA) & HC N ACCEP ⁻	GRADATION	Aggregate: 1 per 2,000 tons or fraction thereof of mix produced (or as specified in the contract).	CP 30	CP 31	CAR Report-Asphalt Quality Level Report (AQL)	Aggregate from the cold feed, pugmill discharge, extraction, or product of CP-L 5120.	See Guidelines for Test Frequency	100 lb. (45 kg) (Agg)
HALT (S ADATIO	MICRO DEVAL	1 per 10,000 tons as specified in the Contract.	CP 30	CPL 4211	Mix Design as per CP 52. CAR - Form 38 Physical Properties Aggregate Test Report.	Aggregate from the cold feed.	Reduction Item 403 - Hot Mix Asphalt.	
RIX ASP GR	FRACTURED FACES AND VOID CONTENT FINE AGGREGATE	As requested by the RME.	CP 30	CP 45 T 304 A	Report on CDOT Form 58. CAR - Form 38 Physical Properties Aggregate Test Report.			Note for all tests: 1 full bag of each aggregate type.
STONE MAT	IN-PLACE DENSITY	All lifts of Item 403: 1 per 500 tons (500 t) or fraction thereof of mix placed (or as specified in the contract). Minimum of 5 tests per project.		CP 44 CP 81 CP 82	Report on CDOT Form 69. Use Form 469 for CP 82 Compaction Test Section. Use CDOT Form 428 or 582.	In the compacted lift.		If LA Abrasion is requested, send 1 additional full bag. Micro Deval cold feed is 1 full bag. 1 full bag is required to get the gradation
	THERMAL SEGREGATION	As specified in the contract.		CP 58	Report on CDOT Form 1346	Behind paver.		needed to perform a "D" Method.
	LONGITUDINAL JOINT DENSITY	1 per 5,000 linear ft. of Joint, or fraction thereof.		CP 44	Report on CDOT Form 1290 Test template CP 44L in SMM.			

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {New Forms designed to	POINT OF VERIFICATION	CENTRAL L. [LOCAL AGENCIES A ACCREDITED LAB, N	RE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
403	THEORETICAL MAX. SP. GRAVITY	1 per 1,000 tons. Minimum of 1 test per day if less than 1,000 tons placed in a day.	CP 41 CP 55	CP 51 CP 56	Report on CDOT Form 69*.	Plant discharge, at/or behind paver.	CHECK TEST: Minimum of each 10K or fraction	50 lb. (23 kg)
:(AM	HVEEM STABILITY		CP 41 CP 55	CPL 5106	See Subsection 106.05, Mix Verification Testing, or for SMA see Project Special Provision,	Plant discharge, windrow, at/or behind paver.	thereof for: Hveem Stability, Air Voids, and VMA. Central Lab will run the Lottman test on	
АЅРНАLТ (НМА):	AIR VOIDS		CP 41 CP 55	CP 44 CPL 5115	Revision of Section 403 Stone Matrix Asphalt Pavement, Sub- section 403.03.	Plant discharge, windrow, at/or behind paver.	See Guidelines for Test Frequency Reduction Item 403 - Hot Mix Asphalt.	
MIX ASP NCE	VOIDS IN MINERAL AGGREGATE		CP 41 CP 55	CP 48		Plant discharge, windrow, at/or behind paver.		
) & HOT MIX / CCEPTANCE	LOTTMAN	1 per 10,000 tons, or fraction thereof. (See Subsection 401.02)	CP 41 CP 55	CPL 5109 CPL 5115		Plant discharge, windrow, at/or behind paver.		
LT (SMA ATION A	HAMBURG WHEEL- TRACKING	1 per project, or mix design change, or as requested by RME. (100 gyrations)	CP 41	CPL 5112	Submit sample to the Euro-Lab Unit of the Central Lab. Applicable with Super-pave	Plant discharge, windrow, at/or behind paver.	1 st 10K or each mix design change, or as requested by the	65 lb. (30 kg) for the Hamburg test
(ASPHA GRAD	FRENCH RUTTING- TESTER	1 per project, or mix design change, or as requested by RME. (100 gyrations)	CP 41	CPL 5114	gyratory compaction designs with 100 design revolutions <u>only</u> .		Region.	65 lb. (30 kg) for the French test.
STONE MATRIX ASPHALT (SMA) & GRADATION ACCI	ASPHALT MIX PERFORMANCE TEST	As requested by RME. 1 st 10K or mix design change only.	CP 41	TBD	Submit sample to the Euro-Lab. Applicable with Super-pave gyratory compaction designs.		As requested by RME	130 lb. (60 kg) for the AMPT.
STONE	PAVEMENT SMOOTHNESS	As specified in contract. Within 14 days after completion of paving.		CP 74	Testing shall be performed by the Contractor, witnessed by the Engineer and data will be immediately transferred to the Central Lab for analysis.		The minimum verification testing will be statewide, once per profiler and 25% of profiles submitted for a profiler.	

400						· · ·	-					
403		/ Item: Asphalt cement/perform	ance grade	d (PG) bind	ers, follow Item 411 of the So	chedule.						
MA)	Incidental Items (n	on-pay):										
F (HMA) PHALT (SI	The Contractor CPL 4209: 1 pe	cceptance Method: CDOT Form shall provide the Engineer with or er 10,000 tons of HMA mix. Obta source per project required.	ne copy of C	ertified Tes	t Reports that is furnished by	<i>r the supplier</i> for Cher omit it to the Central La	nical Tests, per AAS aboratory for testing.	6HTO M 303. Minimum of				
ASPHAL1	One test per 10	ne Contractor shall provide the En ,000 TONS of SMA Mix, per AAS I for SMA including T 88, C 25, an	НТО T 37, a	ind T 90 (T 9	0 is not required when Hydrat	<i>furnished by the sup</i> ed Lime or Hydraulic C	<i>plier</i> per AASHTO N ement is used for Mi	/I 17. ineral Filler).				
HOT MIX TONE MA	plastic index. If	OTE: Mix Design as per CP 52, Submit a 50 lbs. (23 kg) representative sample of each aggregate for testing of aggregate specific gravity, absorption, and plastic index. If Los Angeles (LA) Abrasion or Micro-Deval is also requested for the large aggregate, submit 60 lbs. (27 kg) of the large aggregate. Be sure to document on the CDOT Form 157 which tests are requested.										
AII: HOT MIX ASPHALT (HMA) Including STONE MATRIX ASPHALT (SMA)		NOTE: CAR report-Asphalt Quality Level reports are acceptable Documentation for Asphalt Content, Gradation, In-Place Density, Longitudinal Joint Density, Maximum Specific Gravity, Air Voids, and Voids in Mineral Aggregate.										
ΡΑΥ	TYPE OF TEST	PROJECT VERIFICATION	PROCE	DURES	REMARKS		CENTRAL LA	RE TO USE AN				
ITEM		SAMPLING & TESTING FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	{Forms designed to follow SMM Templates.}	VERIFICATION FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE				
405 円	IN-PLACE DENSITY	1 per 5,000 sq. yds. Or fraction thereof (or as specified in the contract).		CP 44 CP 81 CP 82	Document on CDOT Form 69. Use CDOT Form 428 or 582 for density. Use CDOT Form 469 for CP 82 Compaction Test Section	Roadway behind paver & after rolling.						
HOT-IN-PLACE RECYCLE	MAX. SP. GRAVITY (RICE)	Minimum, 1 per density test.	CP 41	CP 51	Document on CDOT Form 58.							
HOH R	ASPHALT Rejuvenating Agent	See Item 411. <u>COC</u>										

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {Forms designed to	POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIES ACCREDITED LAB	ARE TO USE AN
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
406 யி	IN-PLACE DENSITY	1 per 5,000 sq. yds. Or fraction thereof.	CP 41 * (Meth. C)	CP 53 CP 81	Report on CDOT Form 69 Use CDOT Form 428. *To obtain material for CP 53.	Windrow or roadway, after rolling in the finished roadway. For cationic emulsions, sample after rolling in		
COLD ASPHALT PAVEMENT (RECYCLE)	GRADATION	1 per 20,000 sq. yds. Or fraction thereof.	CP 41	CP 31	Report on CDOT Form 6. Use sieve sizes as required. Use CDOT Form 106.	the finished roadway.		
COLD /	HVEEM STABILITY	1 per 20,000 sq. yds. Or fraction thereof.	CP 41	CPL 5106 modified by CPL 5111	For information only! Use CAR report - Single Sample Asphalt Report (Form 360) for reporting.			
	FREE MOISTURE	1 per day or as specified in the contract.		CP 57				
	ASPHALT Rejuvenating Agent	See Item 411. <u>COC</u>						
	Asphalt Emulsion	See Item 411 <u>COC</u>						
	408 SEALANT JOINT/CRACK JOINT/CRACK JOINT/CRACK JOINT/CRACK JOINT/CRACK JOINT/CRACK JOINT/CRACK		proved (per e ness/apl. Fie	eld-inspect a	nd document that the material			roject Files.

PAY	TYPE OF TEST	T PROJECT VERIFICATION SAMPLING & TESTING	PROCEDURES		REMARKS	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
ITEM		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	{Forms designed to follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
60H SEAL	GRADATION Type I: 3/8" Type II: 1/2" Type IV: 3/4"	1 per 200 tons or 15,000 sq. yds. Or fraction thereof.	CP 30	CP 31	Report on CDOT Form 6. Use CDOT Form 565.	Spreader or the last stockpile before placement as specified in the contract.	1 per project. (See NOTE 1)	33 lb. (15 kg) is approx. 1 full bag by volume. Submit 66 lb. (30 kg) sample of field- produced aggregate to the Central Lab before use. Performance Graded Binder / Asphalt: Follow
Б	LA ABRASION	One per source.	CP 30	T 96 or C 535	Report from CAR – Form 38 Physical Properties Aggregate Test Report		(See NOTE 1)	instructions in Item 411.
	FRACTURED FACES	1 per 1,000 tons or 100,000 sq. yd. Or fraction thereof. Minimum 3 per project	CP 30	CP 45	Report from CAR – Form 38 Physical Properties Aggregate Test Report	Spreader or last stockpile before the spreader as specified in the contract.		65 lb. (30 kg)
	FLAT AND ELONGATED PARTICLES	1 per 600 tons or 50,000 sq. yds. Or fraction thereof, Minimum 3 tests per project.	CP 30	ASTM D4791 Method B	The maximum amount of flat and elongated aggregate with a ratio of 3:1 shall not exceed 12 percent as determined by ASTM D4791. As per 703.05.	Spreader or last stockpile before the spreader as specified in the contract.	(See NOTE 1)	33 lb. (15 kg) is approx.
	COATING TEST	1 per source.	CP 30	CPL 2213	Use CDOT Coating Test worksheet located in CP-L 2213.	Spreader or last stockpile before the spreader as specified in the contract.		

NOTE 1: This Central Lab test can be performed in the Region Lab or the Field Lab if adequate facilities and equipment are available.

411/403	NOTE: Samples 1 thru 5 will be designated Lot No. 1, samples 6 thru 10 will be designated Lot No. 2, samples 11 thru 15 will be designated Lot No. 3.	Point of Verification for Quality <u>Determination</u>
	 ASPHALT CEMENT / PERFORMANCE GRADED (PG) ASPHALT BINDER: Project acceptance samples of Asphalt Cement / Performance Graded Binders will be taken at the Contractor's HMA plant. Samples will be 1 qt. (1 liter) in size in a metallic container and will be sampled per AASHTO T 40. Procedures and Type of Test: PG Binders will be tested according to the test procedures referenced in AASHTO M 320, as modified by Standard Specifications Subsection 702.01(a), and, as a minimum, one sample per lot will be tested for Dynamic Shear Rheometer (DSR) (original). 	< HMA Plant.
	BINDER - When Paid as Item 403: Acceptance Method: CDOT Form 595, required with the Mix Design per CP 52. Project Verification Sampling frequency: 1 sample per 1,000 tons of HMA mix, or fraction thereof, or as specified in the project plans. A complete set of tests to show compliance with the required specifications will be performed at the rate of 1 set of tests per 20,000 tons of HMA mix, with a minimum of 1 complete set of tests per project.	< Storage tank or delivery conveyance.
ASPHALT MATERIALS	BINDER - When Paid as Item 411: Acceptance Method: CDOT 595, required with the Mix Design per CP 52. Project Verification Sampling frequency: 1 sample per 1,000 tons of mix* or fraction thereof, or as specified in the project plans, when bid pay Item is 411 - Asphalt Cement / PG Binder. A complete set of tests to show compliance with the required specifications will be performed at the rate of 1 set of tests per 20,000 tons of mix, with a minimum of 1 complete set of tests per project. For Asphalt cement or binder used other than HMA Mixes, the sampling rate will be one sample per truckload of Binder. Submit <u>all samples</u> to the Central Laboratory where one sample per lot will be randomly tested. Report all sample information on CDOT Form 411 for PG Binder.	< Storage tank or delivery conveyance.
РНАLT	*(In SiteManager/LIMS: An estimate of 1 sample per 50 tons of Binder is used based on 5% AC in the mix; 1 sample per 1,000 tons of mix still governs.)	< At Project site.
ASF	EMULSIFIED ASPHALT: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). Refer to Standard Specifications, Section 702.03. List the information on the form, and note the material is acceptable, then retain it in the Project Files.	
	EMULSIFIED ASPHALT (RECYCLING AGENT) FOR COLD ASPHALT PAVEMENT, ITEM 406: Acceptance Method: Pre-Approved (with Contractor's <u>APL Verification</u> for Documentation). One sample per truckload. Acceptance samples may be taken from the line between the truck and recycling equipment or at the truck. Sample according to AASHTO T 40. Sample size: one liter in a non-metallic container. Submit on CDOT Form 411. Submit all samples to the Central Lab.	< At Project site.
	EMULSIFIED ASPHALT FOR CHIP SEAL, ITEM 409: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for	< At Project site.
	Documentation). One sample per truckload. Sample per AASHTO T 40. Sample size: one liter in a non-metallic container. Submit on CDOT Form 411. Submit all samples in the lot to the Central Laboratory. Note: Fog Coat: Will be calculated on percent residue test.	< At Project site.
	ASPHALT EMULSION FOR PRIME COAT (AEP) (any grade): Acceptance Method: <u>COC</u> . The contractor shall provide the Project Engineer with one copy of a <u>Certificate of Compliance</u> that is <i>furnished by the supplier</i> . List the information on the form and note that the material is acceptable. Retain in Project Files.	
	ASPHALT REJUVENATING AGENT (ARA): Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). Refer to Section 702.04. Submit one sample per project. Sample size: one liter in a non-metallic container. Include supplier/refinery information, type and grade. Submit on CDOT Form 411.	

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING	PROCE	DURES	REMARKS {Forms designed to follow	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
		FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	SMM Templates.	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
412	AIR CONTENT UNIT WEIGHT/YIELD TEMPERATURE SLUMP	Minimum 1 per day then 1 per 5,000 sq. yds. Minimum 3 per mix design.	CP 61 CP 61 CP 61	T 152 T 121 C 1064 T 119	Report test results on CDOT Form 156. Use CDOT Form 626 to notify the contractor & Project Engineer daily with results.	Per CP 61		
PCCP COMPRESSIVE STRENGTH	COMPRESSIVE STRENGTH	* Note 412	CP 61	C 39	Submit cylinders with a CDOT Form 82. Use CAR report: Concrete Compressive Strength Report and CAR report – Concrete Quality Level Report (CQL).	Per CP 61	Cylinders are tested in Central Lab but may be tested in the Field or Region Lab if adequate equipment is available.	1 set of 5 cylinders, Test 2 at 7 days and 3 at 28 days, or as specified in the contract.
COM	WATER CEMENTITIOUS MATERIAL RATIO	1 st three loads each day, then 1 per 2,000 cu. yds. Or fraction thereof.			W/CM = <u>(weight water)</u> (wt. cement + wt. flyash)	Batch ticket.		
	SAND EQUIVALENT	Minimum 1 per day then 1 per 5,000 sq. yds. Minimum 3 per mix design.	CP 30	CP 37		Stockpile or Plant		

*NOTE 412: When compressive or flexural strength specimens are cast, the tests for air content, unit weight/yield, temperature, and slump shall be made on the same sample at the same time.

PAY	TYPE OF TEST			DURES	REMARKS	POINT OF	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
ITEM		SAMPLING & TESTING FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	{Forms designed to follow SMM Templates.}	VERIFICATION FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
412 (continued)	AIR CONTENT	Minimum 1 per day then 1 per 5,000 sq. yds.	CP 61	T 152	Report test results on CDOT Form 156.	Per CP 61		
	UNIT WEIGHT/YIELD TEMPERATURE	Minimum 3 per mix design.	CP 61	T 121 C 1064	Use CDOT Form 626 to notify the contractor & Project Engineer daily with results.			
E	SLUMP	1 per Flexural Strength test.	CP 61	T 119	1			
PCCP FLEXURAL STRENGTH	FLEXURAL STRENGTH	1 per 10,000 sq. yds. per mix. Minimum 3 per mix design and 3 per process for flexural strength tests. * Note 412	CP 61	T 97	Use CDOT Form #83 and CAR report – Concrete Quality Level Report (CQL)	Per CP 61	Beams are tested at the Contractor's Process Control Lab Frequency should be increased to have 1 Owner test per 4 Contractor PC tests.	1 set of 4 beams, tested at 28 days.
	WATER CEMENTITIOUS MATERIAL RATIO	1 st three loads each day, then 1 per 2,000 cu. yds. Or fraction thereof.			W/CM = (weight water) (wt. cement + wt. flyash)	Batch ticket.	•	
	SAND EQUIVALENT	Minimum 1 per day then 1 per 5,000 sq. yds. Minimum 3 per mix design.	CP 30	CP 37		Stockpile or Plant		

*NOTE 412: When compressive or flexural strength specimens are cast, the tests for air content, unit weight/yield, temperature, and slump shall be made on the same sample at the same time.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCE	DURES	REMARKS {Forms designed to follow SMM Templates.}	POINT OF VERIFICATION FOR QUALITY	Jenni Genni Genni Ae	
			PROJECT VERIFICATIO N SAMPLING	PROJECT VERIFICATIO N TESTING		DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
412 (continued)	THICKNESS	Min. 1 per day, per mix. If the project total is < 50,000 sq. yds, a minimum of 10 tests. If the project total is ≥50,000 sq. yds, 1 per 5,000 sq. yds.	T 24	T 148	CAR report – Concrete Quality Level Report. None required on bridge approach slabs.	Hardened concrete.		
EMENT STRENGT	Thickness (Alternate Non- Destructive Gauge)	1 per 1250 linear ft in each lane		T359	Witnessed by Engineer the scanning. Document results	Hardened Concrete		
PORTLAND CEMENT CONCRETE PAVEMENT COMPRESSIVE STRENGTH OR FLEXURAL STRENGTH	PULL TEST for JOINT SEALANTS	Minimum of 6 transverse and 6 longitudinal joint locations for the first 2,500 linear feet of concrete roadway; 3 transverse and 3 longitudinal joints thereafter on the project.		CP 67	Replace joint failures. Report on CDOT Form 389. Document in Project Files. Witnessed by Engineer.	Installed in the hardened concrete joint.		
	DOWEL BAR & TIE BAR PLACEMENT	As specified in Standard Specification Section 412.13 (b).		CP 79	Witnessed by Engineer the MIT scanning. Document results	Joint.		
	PULL TEST for TIE BARS	As specified in Standard Specification Section 412.13 (a).			If stabbed or drilled into the pavement. Witnessed by Engineer.	Hardened concrete.		
	TEXTURE DEPTH	1 per 2500 linear feet or fraction thereof in each lane and shoulder wider than 8 feet at 1 per day.		CP 77B	Summarize and report texture depth on CDOT Form 157.	Hardened concrete.		
	SAW CUT DEPTH	1 per 528 linear feet of each longitudinal joint and 1 transverse joint in a section of 528 ft. or fraction thereof			Summarize and report saw cut depth on CDOT Form 157.	Hardened concrete.		

PAY	TYPE OF	PROJECT VERIFICATION SAMPLING & TESTING				POINT OF VERIFICATION	CENTRAL [LOCAL AGENCIE ACCREDITED LA	S ARE TO USE AN
ITEM	TEST	FREQUENCY	PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
412 (continued)	SAND EQUIVALENT	Minimum 1 per day then 1 per 5,000 sq. yds.	CP 30	CP 37		Stockpile or Plant		
PORTLAND CEMENT CONCRETE PAVEMENT COMPRESSIVE STRENGTH OR FLEXURAL STRENGTH	PAVEMENT SMOOTHNESS *Note	As specified in the contract. Within 14 days after completion of paving.		CP 74	Testing shall be performed by the Contractor, witnessed by the Engineer and data will be immediately transferred to the Central Lab for analysis.		The Central Lab will perform pavement smoothness verification testing. The min. testing will be statewide, once per certified profiler performing work, and 25% of profiles submitted per certified profile.	

*NOTE: Pavement Smoothness is not paid for separately, included in the cost of Concrete Pavement / Square Yard as per CDOT Standard Specifications, Section 412.24.

412	The specified slump is +/- 2 inches of the Lab design slump.
41∠ (continued)	
(,	When compressive or flexural strength specimens are cast, the tests for air content, unit weight/yield, temperature, and slump shall be made on the same sample at the same time.
SSIVE	Compressive Strength specimens shall be initially cured by full immersion in saturated limewater at 73.4° F ± 3° F, with lime concentrations as per AASHTO M 201. Water temperature shall be recorded by a continuous recording thermometer, calibrated every six months; or a maximum-minimum thermometer read and recorded twice a day on CDOT Form 82.
MPRE	When a field laboratory Class 2 is not specified and when approved by the RME, cylinders may be initially cured per AASHTO T23 with a curing temperature of 70° F +/- 10° F. The minimum and maximum temperature of the initial curing shall be recorded.
T CO NGTI	Note: For PCCP Safety Edge, if included with paving as intended, no additional testing will be required.
VEMEN'	INCIDENTAL ITEMS (Non pay) Sealant [Joint and Crack] \Silicone, Joint: Acceptance Method: Pre-Approved with Contractor's <u>AV (APL-Verification)</u> for Documentation). https://www.codot.gov/business/apl.
E PA URA	Backer Rod is not listed on the CDOT APL and is considered a part of the Sealing Joints as an Incidental Item. (CDOT Standard Specification 412.18).
RET	Contraction Joint Plastic Strip: Acceptance Method: Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
CEMENT CONCRETE PAVEMENT COMPRESSIVE STRENGTH OR FLEXURAL STRENGTH	Reinforcing Steel, Dowels Bars, Tie Bars: Acceptance Method: Follow Item 602 of Schedule. <u>COC</u> for Dowels & Tie-bars. Tie-bars are sampled/tested. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Incidental Items not listed above (non-pay): Acceptance Method: Follow Item 601 of Schedule.
EMEN	
ND C ST	
PORTLAND	
POF	

420	Geosynthetics: Acceptance Method: Pre-Approved (with Contractor's (New York APL Verification) for Documentation).
-	Geomembranes. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Reference CDOT Materials Bulletin 2008 No 1.
GEO- SYNTHETICS	https://www.codot.gov/business/designsupport/materials-and-geotechnical/materials-bulletins/Materials%20Bulletin%202008%20No%201.pdf/view Materials shall be selected from the New York Department of Transportation's Approved Products List of Geosynthetic materials that meet the National Transportation Product Evaluation Program (NTPEP) and AASHTO M 288. <u>The web address to ensure product acceptability is</u> Go to A-Z Index, Approved List, Materials and Equipment, Geosynthetics for Highway Construction, Geotextiles . Field-inspect and document that the material is on the New York State APL. https://www.dot.ny.gov/divisions/engineering/technical-services/technical-services-repository/alme/pages/470-1a.html
420	Geotextiles: Acceptance Method: Pre-Approved (with Contractor's <u>New York APL Verification</u> for Documentation).
GEO- TEXTILES	The physical, mechanical, and endurance properties that must be met, or exceeded, by the Geotextile being manufactured must comply with AASHTO M 288, Geotextile Specification for Highway Applications. This Specification covers Geotextile fabrics for use in subsurface drainage, separation, stabilization, erosion control, temporary silt fence, and paving fabrics. Reference: CDOT Materials Bulletin 2008 No 1. https://www.codot.gov/business/designsupport/materials-and-geotechnical/materials-bulletins/Materials%20Bulletin%202008%20No%201.pdf/view Materials shall be selected from the New York Department of Transportation's Approved Products List of Geosynthetic materials that meet the National Transportation Product Evaluation Program (NTPEP) and AASHTO M 288. <u>The web address to ensure product acceptability is</u> Go to A-Z Index, Approved List, Materials and Equipment, Geosynthetics for Highway Construction, Geotextiles
420 SQIRIDS	 Geogrids for Embankment & Roadway: Acceptance Method: <u>COC</u> or <u>CTR</u>. Evaluated on a project-by-project basis by the Engineer of Record and the Regional Materials Engineer. After the specific material recommended for use has been evaluated, if approved for use, then field-inspect and document that the material complies with the project specifications. Certified Test Reports or Certificates of Compliance shall be retained in the Project Files. Geogrids for Mechanically Stabilized Earth (MSE) Walls: Acceptance Method: <u>COC</u> or <u>CTR</u>. Evaluated on a project-by-project basis by the Bridge Design and Management Branch at (303) 512-4072. After the specific material recommended for use has been evaluated, if approved for use, then field-inspect and document that the material complies with the project specifications. Certified Test Reports or Certificates of Compliance shall be retained in the Project Files.

STEEL SHEET 20 PILING	Sheet Piling: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a Certificate of Compliance and Mill Test Reports (furnished by the supplier) showing compliance with Standard Specification Subsection 501.02 (or 501.03 as applicable), Document then retain in Project Files. Document shall state (1) the material has been field-inspected and is acceptable; (2) the Mill Test Reports are on file; and, (3) the heat numbers on piling correspond with the numbers on the Mill Test Reports. Each shipment delivered to the project shall be accompanied by shipping invoices, bar lists, and Mill Test Reports. Reinforced Sheet Piling Tips: Documentation is the same as Sheet Piling. Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
502 SNINI	Steel Piling, Steel Pipe Piling, and Steel Shell Piling: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Follow the instructions in Item 501 of Schedule, except that the material shall comply with Standard Specifications Subsection 502.02. Reinforced Piling Tips: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Tips should be Associated Pile & Fitting Corp. (APF) HARD-BITE HP-77600 for hard rock or equivalent.
DRILLED 5	Concrete: Follow instructions in Item 601 of Schedule.
CAISSONS 6	Reinforcing Steel: Follow instructions in Item 602 of Schedule. NOTE: Do not include quantities listed in Item 602 when reporting.
504	Steel Cribbing: Acceptance Method: CTR.
SUIBBING	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical The Contractor shall provide the Engineer with one copy of Certified Test Reports / Mill Test Reports (furnished by supplier), attach and document on CDOT Form 157, then retain in Project Files. State on CDOT Form 157: (1) the material has been field-inspected and is acceptable. Concrete Cribbing: Follow Items 601 and 602. Timber Cribbing: See Item 508.

504	Reinforcement Elements: Acceptance Method: <u>COC</u> . Buy America Certification (if steel is used): <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
RTH	Facing Elements: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, retain all copies in the Project Files.
ED EAI	Treated Timbers: See Item 508 and document acceptance of the material as stated.
STABILIZED EARTH E) WALL	Structure Backfill: See Item 203, 206, 304, or contract documents as appropriate for gradation, atterberg limits, and density testing. Submit a 55 lb. (22 kg) sample to Central Lab for direct shear testing [AASHTO T 236] to verify the material's friction angle. Submit the required relative compaction and compaction method if friction angle is required. Submit one sample per source.
MECHANICALLY ST (MSE) V	Foundation Soil: Submit a 55 lb. (22kg) sample to Central Laboratory for direct shear testing [AASHTO T 236] to verify the material's friction angle. Submit one sample per 500 feet of wall length if the foundation soil type is unchanged. Submit the required compaction method if friction angle is required. Otherwise, submit one sample for each soil type encountered. If the soil type is the same material as the Structure Backfill, then no additional samples will be required for testing.
MEC	Misc. Items: Document all items in Project Files. The steel used in leveling pad requires a
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	{Forms designed to follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
504	WATER/ CEMENTITIOUS MATERIAL RATIO	Each grout batch mixed.			WCM = (wt. Water) / (wt. cement + wt. Fly ash). Report on CDOT Form 82	Batch Ticket		
	SPECIFIC GRAVITY	Perform with compressive strength.	Baroid Mud (API Method	Balance d RP 13B-1)	Report on CDOT Form 157.			
WALL	COMPRESSIVE STRENGTH	1 per day.	T106 M6 (If sand is used)	C109 M6 (Note1) (If sand is used)	Submit cubes on CDOT Form 82. Report on CDOT Form 192.		Cubes are tested in the Central Lab but may be tested in the Field or Region Laboratory if adequate equipment is available.	

NOTE (1): The cubes are cured 24 hours in the molds and stripped and immersed in lime water until tested.

INCIDENTAL ITEMS (Non-pay)

Miscellaneous Items: Document all items in Project Files.

Water, Non-Potable: Acceptance Method: <u>CTR</u>. Obtain <u>Certified Test Reports</u> from the Contractor (furnished by the supplier) before using. The test shall be per ASTM C 1602. Document that the material is acceptable and retain in Project Files.

Soil Nail Bar: Follow the instruction in item 602 of the Schedule. NOTE: Bar size will be size #11 or smaller.

Bearing Plates, Washers, Nuts, and Couplers: COC. Buy American Certification. Field-inspected and document that the material is acceptable, then retain all copies in the Project Files.

Corrosion Protection (Epoxy Coating): Follow the instruction in item 602 of the Schedule.

Geo-composite Strip Drain and Underdrain: Field-inspected and document that the material is acceptable, then retain all copies in the Project Files.

Miscellaneous Items: Document all items in Project Files.

506 Abrap	 Riprap: Visual-<i>inspect</i> stone to determine compliance with specifications or contract documents, for size, durability, placement, etc. Determine specific gravity (bulk, saturated-surface dry) as specified per AASHTO T 85. Document for each pay item and show quantity represented and that the material has been field inspected and is acceptable. Bed Course Material: Follow instructions in Item 206 of Schedule. Gabions and Slope Mattress: Acceptance Method: <u>COC</u>. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Wire mesh and fabricated baskets. Note that the baskets and wire mesh material have been field-inspected and are accepted on the CDOT Form 157. See Chapter 500 for further details. Concrete and Concrete Reinforced: Follow instructions in Item 601 and 602 of Schedule.
SLOPE AND DITCH PAVING 20	 Concrete and Concrete Reinforced: Follow instructions in Item 601 and 602 of Schedule. See Chapter 600 for more information. Note Initial water cure of cylinders as per Item 601. Welded Wire Mesh: Acceptance Method: <u>COC</u>. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Refer to Standard Specifications Subsection 709.01. Dry Rubble: Determine specific gravity (bulk, saturated-surface dry) as specified according to AASHTO T 85. * Grouted Rubble: Determine specific gravity (bulk, saturated-surface dry) as specified according to AASHTO T 85. * Asphalt: Field test for asphalt content and gradation; 1 each per 500 tons or fraction thereof. No Central Laboratory samples required except for Lottmans. Report on CDOT Form 6 and 58, or computer printouts are acceptable. Include bitumen quantity in Item 403 (Patching) quantities. Follow Item 411 of Schedule. * Document dry rubble and components of grouted rubble in Project Files.
TIMBER 6 STRUCTURES 80	 Treated Timber: Acceptance Method: <u>COC</u>. The Contractor shall provide the Engineer with one copy of the <u>Certificate of Compliance</u> (furnished by the supplier) and a copy of Treating report(s) or Retention assay. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Timber for Cattle Guards: Follow instructions in Item 611 of Schedule. Untreated Timber: <u>Field-inspect</u> and document on CDOT Form 157 that the material is acceptable, then retain all copies in the Project Files.

509	Steel Structures: Acceptance Method: Pre-Inspected. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
STEEL STRUCTURES	See Special Notice to Contractors for details. Final Inspection Report (CDOT Form 193) will be distributed by the Staff Bridge Fabrication Inspectors after all fabrication is complete and all mill test reports are received from the fabricator. This report will include high-strength shop bolts, shop painting, and galvanizing. The Staff Bridge Fabrication Inspectors will determine that the structural steel meets all physical and chemical requirements. Field painting: Field inspect Schedule. Isolated small quantities of structural steel and structural steel-galvanized should be field-inspected and document that the material is acceptable. Structural Steel - Galvanized: The requirements are the same as for non-galvanized steel.
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
STRUCTURAL G PLATE 015 STRUCTURES 0	Structural Plate Structures: Acceptance Method: <u>CTR</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The contractor shall provide the Engineer with one copy of <u>Certified Test Reports</u> (furnished by supplier), Document that the material is acceptable, and then retain in Project Files. The document will require (1) the material has been field inspected and is acceptable, (2) identification numbers on mill test reports corresponds with heat numbers on plates. State on the CDOT Form 157 that the high-strength bolts were field inspected and bear high-strength bolt markings.
512 DEVICE DEVICE	 Type I & II: Acceptance Method: <u>COC</u>. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The contractor shall provide one copy of the <u>Certificate of Compliance</u> and including Certified Test Reports on components. Copies of this <u>Certificate of Compliance</u> are to be attached then retain in Project Files. The document shall state, (1) the material has been field-inspected and is acceptable. Type III: Acceptance Method: <u>CTR</u>. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The contract will list the products and manufacturers specifically approved by the Bridge Design and Management Branch. Field- inspect and document that the material is acceptable, then retain all copies in the Project Files.

PED. & BIKEWAY 5 RAILING 7	Pedestrian & Bikeway Railing: Steel, Aluminum, Timber (any type). Acceptance Method: <u>CTR</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The contractor shall provide the Engineer with one copy of <u>Certified Test Reports</u> (<i>furnished by supplier</i>) to be filed in the Project Files. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
WATERPROOFING C MEMBRANE C	 Prefabricated, Reinforced Membrane: Acceptance Method: <u>COC</u>. Field-inspect and document on CDOT Form 157 that the material is acceptable, then retain all copies in the Project Files. Single Component, Hot Applied, Elastomeric Membrane: Acceptance Method: Pre-Approved (per each batch/lot) (with Contractor's <u>AV (APL Verification)</u> for Documentation). The information available at: <u>https://www.codot.gov/business/apl</u> Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Protective Covering (Roofing paper): Acceptance Method: <u>COC</u>. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Concrete Sealer: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). <u>https://www.codot.gov/business/apl</u> Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
DAMP- PROOFING	Asphalts: Acceptance Method: <u>COC/CTR</u> . Materials for damp-proofing with asphalt shall conform to the requirements ASTM D 449. The contractor shall provide the Engineer with one copy of the Certificate of Compliance or Certified Test Report (furnished by the supplier). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
WATER- PROOFING	Waterproofing Materials: Acceptance Method: <u>COC</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

518	Asphaltic Plug Joints: Acceptance Method: Pre-Approved (per each batch/lot) (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl
NTS	Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. If verification testing is requested by the Engineer, submit one box of the specimen to the Central Lab for testing.
IOF NOIS	Water stops: Acceptance Method: <u>COC</u> . Complies with the Standard Specifications Subsection 518.02. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
S & EXPANSION JOINTS (DEVICES)	Asphaltic Expansion Devices: Acceptance Method: <u>COC</u> . Complies with the Standard Specifications Subsection 518.03. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
TOPS & (DE	Elastomeric Expansion Devices: Acceptance Method: <u>COC</u> . Complies with the Standard Specifications Subsection 518.04. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
WATERSTOPS (I	Modular Expansion Devices : Acceptance Method : <u>COC</u> . Complies with the Standard Specifications Subsection 518.05. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
-	Elastomeric Concrete End Dam: Acceptance Method: <u>COC</u> . Complies with the Standard Specifications Subsection 518.06. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

PAY ITEM	TYPE OF TEST	TEST PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS {Forms designed to	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
601	AIR CONTENT (#1) UNIT WEIGHT (#1) TEMPERATURE	The 1 st three batches at the beginning of a day's production, then one random test per five batches.	CP 61	T 152 T 121 C 1064	Report test results on CDOT Form 156, and CDOT Form 82 when batch correlates to cylinders cast.	Per CP 61.		
	SLUMP (#1)	1 per set of cylinders.	CP 61	T 119		Per CP 61.		
JRAL CONCRETE	COMPRESSIVE STRENGTH	One set of cylinders per 100 cu. yds. or fraction thereof. Test 2 at 7 days and 3 at 28 days. For Class H and HT concrete, one set of cylinders per 100 cu. yds. or fraction thereof. Test 2 at 7 days, 3 at 28 days, and 3 at 56 days.	CP 61	C 39 T 23 (#2)	Submit cylinders on CDOT Form 82. Report on CDOT Form 192.		Cylinders are tested in the Central Lab but may be tested in the Field or Region Laboratory if adequate equipment is available.	

Except for Class BZ concrete, the specified slump is +/- 2 inches of the Lab mix design slump.

2. NOTE (#2): Specimens shall be initially cured by full immersion in saturated limewater, with lime concentrations as per AASHTO M 201. Water temperature shall be recorded by a continuous recording thermometer, calibrated every six months; or a maximum-minimum thermometer read and recorded, twice a day, on the CDOT Form 82 When a field laboratory Class 2 is not specified and when approved by the RME, cylinders may be initially cured per AASHTO T23 with a curing temperature of 70° F +/- 10° F. The minimum and maximum temperature of the initial curing shall be recorded.

INCIDENTAL ITEMS (Non-pay)

Reinforcing Steel: Follow instructions in Item 602 of the Schedule.

Water, Non-Potable: Acceptance Method: CTR. Obtain Certified Test Reports from the Contractor (furnished by the supplier) before using. The test shall be per ASTM C 1602. Document and retain in Project Files.

Other Additives: Additives included in the approved Mix Design require no additional documentation per Materials Bulletin 2017 Number 1, dated August 23, 2017.

Curing Compounds: Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation). https://www.codot.gov/business/apl

Tabulate the quantity of material used on the project. If you have questions or problems, contact eric.prieve@state.co.us or 303-398-6542.

601	INCIDENTAL ITEMS (Non-pay)
	Epoxy Adhesive: Acceptance Method: Project by Project Approval only, No longer listed on the CDOT Approved Products List.
	For Structural Bridge Adhesives use Staff Bridge SME Guidance. Staff Bridge SME: greg.marcuson@state.co.us
	Expansion Joint Material, Preformed Filler: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
Ë	Cementitious Grouts: Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation).
CRE	https://www.codot.gov/business/apl
NO	Class 5 Masonry Finish: Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation).
AL O	https://www.codot.gov/business/apl
STRUCTURAL CONCRETE	Structural Concrete Coating (Acrylic): Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation) Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
RUC	https://www.codot.gov/business/apl
ST	Structural Concrete Sealer: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation) Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	https://www.codot.gov/business/apl
	Bridge Deck Forms; Permanent (left in-place) Steel: Acceptance Method: CTR.
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
	The contractor shall provide the Engineer with one copy of <u>Certified Test Reports</u> furnished by the supplier. Document and state (1) the material has been field-inspected and is acceptable, (2) Certified Test Reports are on file.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection 602 Reinforcing Steel (black bar) & Epoxy-Coated Reinforcing Steel (coated bar): Acceptance Method: Pre-Approved (with Contractor's QML Verification for Documentation). COC with all applicable Mill locations documented. Buv America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Per CP 11 the Contractor shall only use qualified manufacturer sources of reinforcing steel found on the QML at: https://www.codot.gov/content/apl/SteelReinforcingBarsAndSteelDowelBars.pdf. https://www.codot.gov/content/apl/EpoxyCoatingForReinforcingSteel.pdf Each shipment delivered to the project shall be accompanied by shipping invoices, bar lists, and Mill Test Reports. These reports are to be retained in the Project Files during construction. The document shall state (1) that the steel mill is on the QML (2) the material has been field-inspected and is acceptable, REINFORCING STEEL (3) Mill Test Reports are on file, and (4) a tabulation of the quantity used on the project. Verify that the bar markings match the source listed on the Mill Test Report. A bar marking identification guide reference is in Chapter 600. Note: Information on bar markings at CRSI website: http://www.crsi.org/index.cfm/steel/identification Samples of reinforcing steel shall be submitted to the Central Lab for testing from each approved Mill location delivered to the project. Each sample shall consist of three straight bars, 3-4-feet long of the same grade and size randomly selected by CDOT from bars delivered to the project. The bar size will be size #10 or smaller. CDOT will take possession after the Contractor has cut them to the proper length. Samples are based on Mill location regardless of it being black bar or epoxy coated. (DO NOT SEND IN MULTIPLE SIZES OF BARS FROM THE SAME MILL LOCATION. Tie bars used in Item 412 concrete paving shall submit 3 samples for testing per mill location.) LOCAL AGENCIES ARE TO USE AN AASHTO ACCREDITED LAB. Note: "Test bars" delivered to the project by the supplier are not random samples and should not be used for acceptance. CSRI Plant Identification Guide for Concrete Reinforcing Bars: For further information contact edward.trujillo@state.co.us 303-304-3468 This resource is no longer available as it used to be. It is part of a field inspection guide and can be purchased at CRSI for \$25.00: http://resources.crsi.org/resources/field-inspection-of-reinforcing-bars-guide/ There is also a CRSI app on the Google and Apple app stores. The mill identification part of the guide is \$3 per user. http://resources.crsi.org/resources/rebar-reference-mobile-app/ Steel Chairs: Acceptance Method: COC. Buy America Certification. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

603	Corrugated Steel Pipe (CSP) and End Sections. Corrugated Aluminum Pipe (see note). Bonded CSP. Bituminous Coated CSP and Pre-Coated CSP: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field inspect for visible defects. Tabulate final quantities. Total quantities must equal or exceed final project quantities. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Note 1: Ensure that the heat numbers in the COC correspond with the heat numbers on the field inspected pipe. Cast-in-Place Concrete Pipe: Follow instructions in Item 601 of Schedule. (ASSHTO T 23 Note # 2)
S	Initial water cure as per Item 601, or as directed by the Engineer. Concrete Pipe and Precast Concrete Box Culvert: Acceptance Method: Pre-Approved (with Contractor's <u>QML Verification</u> for Documentation). Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
CULVERTS AND SEWERS	Per CP 11 the Contractor shall only use qualified manufacturer sources of precast concrete products found on the website at: https://www.codot.gov/content/apl/PrecastConcreteStructures.pdf Field-inspect for visible defects. Tabulate final quantities. Total quantities must equal or exceed final project quantities. Field-inspect and document that the material is acceptable, retain all copies in the Project Files.
JLVERTS A	Thermoplastic Pipe: Acceptance Method: <u>COC</u> . Pipe types can include PVC, (PE) Polyethylene. <u>Must have Steel End Section or as approved by the Engineer</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
บ	HDPE Pipe & Polypropylene Pipe: Acceptance Method: COC. (Note: Manufacturing facility must have COC from NTPEP, see Special Notice to Contractors.)
	Vitrified Clay Pipe: Acceptance Method: <u>COC</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Gaskets: Acceptance Method: <u>COC</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Pipe Joint-Sealing Compounds: Acceptance Method: <u>COC</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Note 2: See the M Standards for proper types of End Sections when using an Aluminum pipe.
	https://www.codot.gov/business/designsupport/2019-and-2012-m-standards

604	Manholes, Inlets, Meter Vaults, and Precast Concrete Units (Prefabricated): Acceptance Method: Pre-Approved (with Contractor's <u>QML Verification</u> for Documentation).
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
TS, LTS	Per CP 11 the Contractor shall only use qualified manufacturer sources of precast concrete products found on the website at: https://www.codot.gov/business/apl/qualified-manufacturers-list.html
S, INLE ⁻ Er vaul	Field Fabricated: Concrete, follow Item 601. Note Initial water cure as per Item 601, or as directed by the Engineer. Reinforcing Steel, follow Item 602. Field- inspect and document that the material is acceptable, then retain all copies in the Project Files.
MANHOLES, INLETS, AND METER VAULTS	Clay or Shale Brick, Concrete Brick, Concrete Masonry Blocks: Acceptance Method: <u>COC</u> . Must meet individual specifications though not paid for separately. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Inlet Grates and Frames, Manhole Rings, Covers, and Steps: Acceptance Method: COC.
	Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Must meet individual specifications though not paid for separately. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
605	Corrugated Metal Pipe: Acceptance Method: <u>COC</u> .
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical
	Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
JB-SURFACE DRAINS	Vitrified Clay Pipe: Acceptance Method: <u>COC</u> . Follow instructions in Item 603.
SURI	Plastic Pipe: Acceptance Method: COC. Field-inspect and document that the material is acceptable, retain all copies in the Project Files.
SUB- D	Bedding and Filter Materials: Follow instructions in Item 206 of Schedule. See Chapter 200 for filter material information.

606	Type 3: Treated Timber Posts and Blocks. Acceptance Method: <u>COC</u> . The Contractor shall provide one copy of a Certificate of Compliance (<i>furnished by the supplier</i>). POSTS MUST BE FIELD INSPECTED (size, straightness, overall quality, visible defects, etc.). Document, List source, quantity, and sizes.
	Guardrail Block, Synthetic. Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation) https://www.codot.gov/business/apl
	Steel Posts for Type 3 (All types) - Document same as Guardrail below.
GE RAIL	Hardware, End Anchorage and Transitions - Acceptance Method: <u>COC</u> . Buy America Certification: List each pay item type, Field-inspect, and document that the material is acceptable, then retain all copies in the Project Files. (For Concrete Transitions Follow Instructions in Item 601 and 602.) <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u>
k BRID	Cable Barrier - Acceptance Method: <u>COC</u> . Buy America Certification: The contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> and Mill Test Reports (<i>furnished by supplier</i>) to be filed. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
ARRIER 8	Midwest Guardrail System Type 3 (W-Beam Galvanized) - Acceptance Method: <u>COC</u> . Buy America Certification: The contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> and Mill Test Reports (<i>furnished by supplier</i>) to be filed. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
GUARDRAIL, CABLE BARRIER & BRIDGE RAIL	Bridge Rail Type 8R MASH, and Type 10 MASH: Acceptance Method: <u>COC</u> . <u>Buy America Certification</u> . The Contractor shall furnish the Engineer with one copy of <u>Certificate of Compliance</u> (furnished by the supplier) including <i>Mill Test Reports</i> . Field-inspect and document that the material is acceptable, retain all copies in the Project Files.
RAIL,	Note: Ensure that the heat numbers in the COC correspond with the heat numbers on the field inspected guardrail. For assistance contact Subject Matter Expert: CDOT Staff Bridge
ARD	https://www.codot.gov/business/designsupport/bulletins manuals/cable-barrier-guide/cable-barrier-guide/view
GU	Type 7, Precast: Acceptance Method: Pre-Approved (with Contractor's <u>QML Verification</u> for Documentation). Buy America Certification: The Contractor shall provide a copy of a <u>Certificate of Compliance</u> (furnished by the supplier), document, and retain all copies in the Project Files.
	Per CP 11 the Contractor shall only use qualified manufacturer sources of precast concrete products found on the website at: <u>https://www.codot.gov/business/apl/qualified-manufacturers-list.html</u>
	Type 9, Cast-in-Place: Follow Item 601 of Schedule, except that the test frequency for compressive strength shall be 1 per 1,000 linear feet. NOTE: Initial water cure as per Item 601, or as directed by the Engineer.

606	Reinforcing Steel (Epoxy Coated): One sample of reinforcing steel shall be submitted to the Central Lab from each approved source. The sample shall consist of three straight 3-4-foot-long pieces of the same grade and size. The bar size will be size #10 or smaller.
	NOTE: If Chromium or Stainless-Steel is to be tested, Contact tony.roffe@state.co.us CDOT Headquarters North Holly Central Concrete Laboratory Manager for testing information.
RAII	Incidental Items (non-pay) - Follow instructions in Section 601 of this Schedule.
RIDGE	Light Weight Aggregates - Follow Section 601 of this Schedule, except that Central Laboratory sample size shall be one full sample bag.
R BF	Glare Screens: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). <u>https://www.codot.gov/business/apl</u>
CABLE BARRIER & BRIDGE RAIL	
E BAF	
CABL	
GUARDRAIL,	
GU	

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection 607 Barbed Wire: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Each roll shall be tagged with legible markings bearing the following information. ASTM Designation A 121, Design No., Class of Coating, Length of Roll, and Name of Manufacturer. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Woven Wire: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Each roll shall be tagged with legible markings bearing the following information. ASTM Designation A 116, Design No., Class of Coating. Length of Roll, and Name of Manufacturer and document this information. Gates, Wire Ties, Wire Stays, Clips, Clamps, Staples, and Miscellaneous Fittings: Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Chain Link Fabric: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. FENCES Steel Posts. Steel Pipe Railing: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Make a random check and document the weight, length, and coating. Field-inspect and document that the material is acceptable as per the Project Plans. then retain all copies in the Project Files. As per CDOT Standards and Specification Section 707.01. Timber Posts (Treated): Acceptance Method: COC. POSTS MUST BE FIELD INSPECTED (size, straightness, etc.). Document listing source, number, and sizes. Timber Posts (Untreated): Acceptance Method: COC. Field-inspect and document listing the source, number, and sizes. Footing or Bases Small Projects: Acceptance Method: COC. M-607-1 Concrete Shall be Class B. Concrete with Lightweight Aggregates conforming to AASHTO M195 (ASTM C330) will be permitted. Noise Wall: Acceptance Method: Pre-Approved (with Contractor's AV (APL Verification) for Documentation). https://www.codot.gov/business/apl The Contractor shall provide the Engineer with one copy of Certified Test Reports (furnished by the supplier) to validate the structural values required of the wall. Field-inspect that the material is acceptable, then retain all copies in the Project Files. Contact the CDOT Staff Bridge SME: joel.johnson@state.co.us for the structure requirements. Contact the CDOT Traffic Safety Subject Matter Expert for highway safety structures. Contact the CDOT Air Quality and Noise Program Manager SME rose waldman@state.co.us for the acoustic gualities' guidance.

608	Truncated Dome / Detectable Warning Plate: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl
CURB RAMP	Buy America Certification (if cast iron or steel): https://www.codot.gov/business/designsupport/materials-and-geotechnical
OR	Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Reference CDOT M-Standards M-608-1.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS {Forms designed to	POINT OF VERIFICATION FOR	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
608	AIR CONTENT	1 per 1,000 sq. yd. (840 m²) or fraction thereof.	CP 61	T 152	Report on CDOT Form 156.	Per CP 61.		
WAYS	UNIT WEIGHT/YIELD TEMPERATURE	One per set of cylinders.	CP 61	T 121 C 1064				
) BIKE	SLUMP	One per set of cylinders.	CP 61	T 119				
SIDEWALKS AND BIKEWAYS (PCCP)	COMPRESSIVE STRENGTH	1 set of 5 cylinders per 1,000 sq. yds. (840 m²) or fraction thereof. Test 2 at 7 days and 3 at 28 days.	CP 61	C 39	Submit cylinders on CDOT Form 82. Report on CDOT Form 192. Initial water cure as per Item 601, or as directed by the Engineer.	Per CP 61.		
	Slump and air	each day's production, the first load c content tests are required for each se n-pay): Follow instructions in Item 6(et of cylinders	s for all Classe	r air content. If the test meets spe is of concrete. The specified slu	cifications, then revert to the mp is +/- 2 inches of the La	testing frequency a b mix design slun	ibove. 1 p.
KEWAYS	ASPHALT CONTENT	1 per project if the planned quantity is more than 2,500 tons.	CP 41 CP 55	CP 85 CPL 5120	Mix Design as per CP 52; CDOT Form 43 required <u>before</u> the mix is produced. Report Asphalt Content on Form 58.	See Item 403	See Item 403	See Item 403
SIDEWALKS AND BIKEWAYS (HMA)	GRADATION	1 per project if the planned quantity is more than 2,500 tons.	CP 30	CP 31	Report Gradation on CDOT Form 6	See Item 403		
SIDEWAL	IN-PLACE DENSITY	1 per project if plan quantity is more than 2,500 tons		CP 44 CP 81	Report on CDOT Form 69	See Item 403		

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS {Forms designed to	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
609	AIR CONTENT	1 per 2,000 lin. ft. (600 m) or fraction thereof.	CP 61	T 152	Report on CDOT Form 156.	Per CP 61.		
Ŕ	UNIT WEIGHT/YIELD TEMPERATURE	One per set of cylinders.	CP 61	T 121 C 1064				
	SLUMP	One per set of cylinders.	CP 61	T 119				
CURB AND GUTTER (PCCP)	COMPRESSIVE STRENGTH	1 set of 5 Cylinders per 2,000 lin. ft. (600 m) or fraction thereof. Test 2 at 7 days and 3 at 28 days.	CP 61	C 39	Submit cylinders on CDOT Form 82. Report on CDOT Form 192 Initial water cure as per Item 601, or as directed by the Engineer.	Per CP 61.		
	Slump and air	each day's production, the first load o content tests are required for each se 1-pay): Follow instructions in Item 60	t of cylinders	for all Classe	air content. If the test meets spe s of concrete. The specified slum	cifications, then revert to p is +/- 2 inches of the La	the testing frequency a b mix design slump.	bove.
CURB AND GUTTER (HMA)	ASPHALT CONTENT	1 per 2,500 lin. ft. (30 tons) or fraction thereof or 1 per Mix Design as required by the project.	CP 41 CP 55	CP 85 CPL 5120	Mix Design as per CP 52; CDOT Form 43 required <u>before</u> the mix is produced. Report Asphalt Content on Form #58.	Plant discharge, at/or behind the paver. For Central Lab Correction Factor, sample aggregate from belt and Binder from Contractors tank.	See Item 403	See Item 403
	GRADATION	1 per 2,500 lin. ft. (30 tons) or fraction thereof. or 1 per Mix Design as required by the project.	CP 30	CP 31	Report Gradation on CDOT Form 6	Aggregate from the cold feed, pugmill discharge, extraction, or product of CP-L 5120.		

610	Asphalt: Conforms to Item 403 (SEE Section 610.02)						
	Decorative Concrete and Patterned Concrete: Follow instructions in Item 608 of this Schedule.						
	Median Edging (Patterned Concrete): Follow instructions in Item 609 of Schedule.						
VER	NOTE: Submit a Median Cover Material mix design documenting adherence to Special Provisions or contract documents.						
N CO ERI≜	NOTE: Initial water cure as per Item 601, or as directed by the Engineer.						
MEDIAN COVER MATERIAL	Aggregate: Sample according to CP 30 and test for gradation according to CP 31. Test frequency 1 per 1,000 tons or fraction thereof. Report on CDOT Form 6. Points of Acceptance: In stockpile or placed layer.						
	Stone: Paid by the ton (metric ton). Field inspect for compliance with Special Provisions or contract documents. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Herbicide Treatment: Follow instructions in Item 217 of this Schedule. Use under the aggregate or under the stone.						
611	Precast Cattle Guard Boxes: Acceptance Method: Pre-Approved (with Contractor's QML Verification for Documentation).						
	Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical						
ыS	Per CP 11 the Contractor shall only use qualified manufacturer sources of precast concrete products found on the website at:						
CATTLE GUARDS	https://www.codot.gov/business/apl/qualified-manufacturers-list.html						
บ อ	The Contractor shall provide a copy of a <u>Certificate of Compliance</u> (furnished by the supplier), Document that the material is acceptable then retain all copies in the Project Files.						
	Concrete, Reinforcing Steel, Structural Steel, and Treated Timber: Follow instructions for 601 and 602 of this Schedule. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						

612	Delineators:	Steel Posts: Acceptance Method: <u>COC</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u>
RS &)RS		Make a random check of weight, length, and condition of coating as per CDOT Standard Plan No. S-612-1. Field-inspect as per the project plans and document that the material is acceptable, then retain all copies in the Project Files. <u>https://www.codot.gov/business/apl</u> Contact Staff Traffic Product Evaluation Coordinator/Subject Matter Expert: edward.truillo@state.co.us or esayas.butta@state.co.us for further information
DELINEATORS REFLECTORS	Reflectors:	Acceptance Method: Certificate of Compliance (COC). Field-inspect as per CDOT S-Standards S-612-1, and document that the material is acceptable, then retain all copies in the Project Files Note: The CDOT APL does not currently have approved products listing for Traffic Control\Reflective Element\Delineator Post Marker. Contact Staff Traffic PEC/SME: edward.truillo@state.co.us or esayas.butta@state.co.us for further information on the Delineator Post Marker.
	Delineators:	Flexible Posts - <i>Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. https://www.codot.gov/business/apl</i>
	Median Barri	ier Reflectors: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. https://www.codot.gov/business/apl

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection 613 Luminaire: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a Certificate of Compliance (furnished by supplier) to be filed. Field-inspect and document that the material is acceptable, retain all copies in the Project Files. Wiring: Acceptance Method: COC. Field-inspect for compliance with plans and specifications. Document in Project Files. Anchor Bolts: Acceptance Method: CTR. The Contractor shall provide the Engineer with one copy of Certified Test Reports (furnished by supplier) to be filed. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Metal or Plastic Conduit: Acceptance Method: COC. Buy America Certification (for metal only): https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Light Standards, High Mast: Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Includes poles, luminaries, rings, lowering devices, electrical components. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Breakaway couplers and bases: Field-inspect as per CDOT Standards and Specifications 715.03(a), and document that the material is acceptable, then retain all LIGHTING copies in the Project Files. **Light Standards, Precast Concrete or Concrete Cast in-place: Acceptance Method: <u>COC</u>. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. *NOTE: For any concrete cast-in-place, if cylinders are fabricated, then initial water cure as per Item 601, or as directed by the Engineer. Light Standards, Metal (poles and arms): Acceptance Method: COC. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Hardware for Metal Light Standards: Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Note: When light standards (poles and arms) are paid for under Item 613, a Certificate of Compliance for all structural components including light standards, bases, couplers, anchor bolts, luminaries, and other attachments shall state that the components will safely resist the higher of a 100 miles per hour wind velocity (Section 715.03 (a)) or the wind velocity specified in the plans or specifications or contract documents. The Certificate of Compliance shall state that static tests have been performed. If the Certified Test Reports are not in the Project File with CDOT, they must be attached to the Certificate of Compliance. The test procedure for aluminum parts shall satisfy the requirements of the Aluminum Association, Inc., "Specifications for Aluminum Structures" Section 8, except that no reduction factors for live load and dead load will be permitted. The Certificate of Compliance for breakaway couplers and bases shall state that production lot samples have been tested and meet the breakaway requirements of the AASHTO Standard Specifications for Structural Supports for Highway Signs, Luminaires, and Traffic Signals, Section 7.

614	Sign Panels: Acceptance Method: <u>COC</u> . Buy America Certification (for steel only, not aluminum or composite): https://www.codot.gov/business/designsupport/materials-and-geotechnical						
	The Contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (furnished by supplier) to be filed. After arrival on the project, field-inspect fabricated panels for correct sign wording, legend, and workmanship. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Retroreflective Sign Sheeting: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl						
	Signposts - Steel, Wide Flange (WF): Acceptance Method: <u>COC</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (furnished by supplier) to be filed. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Signposts- Concrete small projects: Acceptance Method: <u>COC</u> . Reference S-614-9 Concrete Class B.						
EVICES	U2 Type: Acceptance Method: <u>COC</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Make a random check of weight, coating, and length for plan requirements. Square Tube Posts may be used as an alternate. See Standard Drawing for post sizes. Field-inspect and document the material is acceptable, then retain all copies in the Project Files.						
OL D	Timber: Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
TRAFFIC CONTROL DEVICES	Overhead Sign Structures: Acceptance Method: <u>CTR</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The Contractor shall provide the Engineer with one copy of a <u>Certified Test Report(s)</u> and Certified Mill Test Reports for all steel materials incorporated into the structure (furnished by supplier). Field- inspect and document that the material is acceptable, then retain all copies in the Project Files.						
TRA	Traffic Signal Structure(s): Acceptance Method: CTR. Buy America Certification: https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the Engineer with one copy of a https://www.codot.gov/business/designsupport/materials-and-geotechnical The contractor shall provide the structure (<i>furnished by supplier</i>). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Anchor Bolts: Acceptance Method: <u>CTR</u> . The contractor shall provide the Engineer with one copy of a <u>Certified Test Report</u> (furnished by supplier). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Concrete Footings: Concrete and Reinforcing steel. For large quantities, if cast-in-place cylinders are required, document per Item 601. If Cast-in-Place, initial water cure as per Item 601, or as directed by the Engineer. See the end of the Schedule for small quantities. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.						
	Construction Traffic Control Signing & Devices: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl						

614 Continued	Lighting Fixtures, Flashing Yellow Beacons, Traffic Signal Systems: Acceptance Method: <u>COC</u> Field-inspect for compliance with plans and specifications, and if in doubt, contact Region Traffic Signal Technician / Foreman. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Messenger Cables, Electrical Conduit, Pull Boxes, Direct Burial Cable, Vehicle Detector Wire Loop, Grounding and Bonding, Miscellaneous Hardware, and Barricades: <u>Field-inspect</u> and document that the material is acceptable, then retain all copies in the Project Files
TRAFFIC CONTROL DEVICES	Breakaway Sign Structures: Acceptance Method: <u>COC</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.

WATER CONTROL 9 DEVICES	 Headgates and Parshall Measuring Flumes: Acceptance Method: <u>COC</u>. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> The Contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (by supplier). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. Embankment Protectors: Follow instructions in Item 603 of Schedule. Follow individual Item specifications for any other type.
616	Siphon Pipe (metal and concrete), Siphon Drain Pipe: Follow instructions in Item 603 of Schedule.
SIPHONS	 Trash Guards, Drain Valves, Valve Boxes: Field-inspect and document that the material is acceptable, then retain all copies in the Project Files. See Standard Specifications Subsection 712.06 and 716.07. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Gaskets: Follow instructions in Item 603 of Schedule.
PRESTRESSED CONCRETE 9 (STRUCTURES) 8	Pre-stressed Concrete Unit: Acceptance Method: Pre-Inspected. Buy America Certification: https://www.codol.gov/business/designsupport/materials-and-geotechnical A final report (CDOT Form 193) will be issued by the Staff Bridge Fabrication Inspectors stating that the units comply with the specifications and that the Material reports are on file at CDOT. Call the CDOT Staff Bridge Fabrication Inspectors at (303) 757-9339 for information. Prestressed and Pre-Inspected Girder members (units) will bear a CDOT starp. Girder members will be stamped by CDOT personnel or the designated agent when Quality Assurance determines that the contract requirements have been met. CDOT's Staff Bridge Fabrication Inspectors will notify the Project Engineer or project personnel of any release of girder members planned before the 28-day normal release schedule or specified in the contract documents. Post-Tensioned Members: (*) All components must meet individual specifications. Post-tensioning data must be documented in Project Files. Concrete - follow instructions in Item 601 of Schedule: except that one set (5) of cylinders are required for each concrete placement. Concrete usually is cast-in-place. See note in Item 601 for curing instructions. Reinforcing Steel: Follow instructions in Item 602 of Schedule. Field Post-Tension Elements: (1) Strand, wire, and bars may be pretested. If not pretested contact Central Laboratory immediately and submit samples at the required frequencies. The Contractor shall provide the Project Engineer with one copy of <u>Mill Test Reports</u> . These reports are to be filed with the Project Documents: (1) the material has been field-inspected and is acceptable, (2) Mill Test Reports are filed, and (3) a tabulation of the quantity used on the pr
	(*) Sampling Frequency: Strand 1-per Source (Sample 5.5 ft. (1.7 m) long). Include a copy of the <u>Mill Test Report</u> Bars 1 per 5 ton (5 t) or fraction thereof (sample 42" (1070 mm) long). Bars with a diameter greater than 1½ inches will be accepted with a <u>Certified Test Report</u> .

619	Cast Iron and Copper Pipe: Acceptance Method: COC. Buy America Certification. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
WATER LINES	Welded Steel Pipe: <u>Field-inspect</u> and document that the material is acceptable, then retain all copies in the Project Files. Welding is performed in the field as per AWS, D-1.1.
	Standard Galvanized Pipe: Acceptance Method: <u>COC</u> . <u>Buy America Certification.</u> Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
WATE	Thermoplastic Pipe: Acceptance Method: <u>COC</u> . <u>Field inspect PVC or PE pipe for pressure rating, brand name, and NSF rating upon arrival and before</u> <u>use</u> . You must carefully check for NSF rating on the pipe when the plastic pipe is used for potable and city waterline and domestic consumption. Field-inspect and document that the material is acceptable, retain all copies in the Project Files.
	Valves and Valve Boxes: Acceptance Method: <u>COC</u> . <u>Buy America Certification</u> . Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
622	Precast Concrete Units, Light Poles, Picnic Tables, and Septic Tanks: Acceptance Method: <u>COC</u> . <u>Buy America Certification</u> . Follow Certificate of Compliance procedure.
	Structural Glazed Tile, Ceramic Tile, Interior Insulation, Copper Pipe, Cast Iron Pipe, Perforated Drainpipe: Acceptance Method: <u>COC</u> . The Contractor shall provide the Engineer with one copy of a <u>COC</u> (<i>furnished by supplier</i>). Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
S	Roofing Asphalt: Acceptance Method: <u>COC</u> . The Contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (furnished by the supplier) stating conformance to ASTM D 312, Type I and III. List all information on CDOT Form 411 that the material is acceptable and retain all copies in the Project Files.
REST AREAS AND BUILDINGS	Brick, Concrete Brick, Concrete Block: Check manufacturer, style, number, and color. The contractor shall provide the Engineer with one copy of a <u>Certified</u> <u>Analysis</u> to be filed with documents and retained in Project File. Document that the material has been field-inspected and is acceptable, and that the Certified Analysis is on file. If no Certified Analysis is available, submit 5 brick or block per 10,000 or fraction thereof to the Central Laboratory before use.
RE: AND	Mortar Sand: Submit one 33 lb. (15 kg) sample to Central Laboratory before use. Document that the material is acceptable, then retain all copies in the Project Files.
	Masonry Cement: Must be a commercial brand in good condition. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
	Leaching Field Aggregate: Field-inspect and field test to determine compliance with plans and specifications. One field sieve analysis is required for every 100 cubic yards or fraction thereof. Report on CDOT Form 6.
	ALL ITEMS NOT INCLUDED ABOVE: Document that the material is acceptable, then retain all copies in the Project Files.

IRRIGATION 9 SYSTEM 20	Irrigation System: Acceptance Method: <u>COC</u> . The Contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (furnished by supplier) to be filed. Field-inspect and document that the material is acceptable, then retain all copies in the Project Files.
624	Drainage Pipe: Acceptance Method: <u>COC</u> . Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u>
DRAINAG E PIPE	See Item 603 of the Schedule. Note: Item 513 that was discontinued is incorporated into this Section.
PAVEMENT MARKING 25	 Glass Beads: Acceptance Method: <u>CTR/COC</u>. All post-consumer(recycled) and industrial produced glass beads for pavement marking shall have been manufactured or recycled from North American glass waste streams in the United States of America. The bead manufacturer/supplier shall submit a Certificate of Compliance (COC) in accordance with CDOT Standard Specifications Subsection 106.12 confirming that North American glass waste streams in the United States of America were used in the manufacture of the glass beads, and a Certified Test Report (CTR) for Glass Beads per CDOT Standard Specifications, Section 713.08, and Table 713-2. Pavement Marking, All Types: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation).
	<u>https://www.codot.gov/business/apl</u> NOTE : Field-inspect that the material is acceptable, then retain all copies in the Project Files.
PEDESTRIAN BRIDGES 8	 Pedestrian Bridges: Acceptance Method: <u>COC</u>. Buy America Certification: <u>https://www.codot.gov/business/designsupport/materials-and-geotechnical</u> Established through a Project Special. The Contractor shall provide the Engineer with one copy of a <u>Certificate of Compliance</u> (<i>furnished by the supplier, if applicable</i>) <i>and Mill Test Reports</i>. Individual components should be inspected and documented where possible. Follow the schedule for the appropriate item, (e.g. concrete, timber, etc.) If the bridge is: Pay Item 628 CIP, and you are unable to identify parts, or if it is precast or prefabricated at an off-site location, then field inspect for adherence to the plans and specifications or special provisions, as applicable. Document on appropriate CDOT forms, listing what material items can be readily identified.

PAY ITEM	TYPE OF TEST	PROJECT VERIFICATION SAMPLING & TESTING FREQUENCY	PROCEDURES		REMARKS	POINT OF VERIFICATION	CENTRAL LAB (CL) [LOCAL AGENCIES ARE TO USE AN ACCREDITED LAB, NOT CDOT CL]	
			PROJECT VERIFICATION SAMPLING	PROJECT VERIFICATION TESTING	{Forms designed to follow SMM Templates.}	FOR QUALITY DETERMINATION	TEST FREQUENCY	SAMPLE SIZE
641 SHOTCRETE	COMPRESSIVE STRENGTH AIR CONTENT	1 per day if less than 50 cu. yds. are placed. Once per 50 cu. yds. or fraction thereof. 3 cores tested at 28 days. The 1 st three batches at the beginning of a day's production, then 1 per 50 cu. yds. or fraction thereof.	C 1140 CP 61	C 1140 T 24 T 152	Coring of shotcrete panels shall be performed by the contractor. If 28-day strengths are below specified strength, three additional cores will be tested at 56 days. Cores must be delivered to the testing facility 1 workday before the date of the required test for sulfur capping. Only for the wet process.	Panels shall be field cured. Cores for 28- day strengths are removed 25-27 days after casting. Cores for 56-day strengths are removed 53-55 days after casting.		
708 Faints	Structural Steel Bridge Paint: Acceptance Method: <u>COC</u> . Inorganic Zinc-Rich Polyurethane System. The Contractor shall provide the Engineer with one copy of a <u>Certificate of</u> <u>Compliance</u> (furnished by the supplier or manufacturer) stating that the material complies with Standard Specifications Section 708 and specific requirements stated in the project plans. This information to be filed. Retain in Project Files. Structural Concrete Coating: Acceptance Method: Pre-Approved (with Contractor's <u>AV (APL Verification)</u> for Documentation). https://www.codot.gov/business/apl https://www.codot.gov/business/apl							

Guidelines for Test Frequency Reduction

SCOPE:

Some relaxation in inspection and testing procedures may be permitted under certain conditions. Reduced engineering control may be particularly applicable to small quantities of intermittently delivered material on large projects and for contracts covering small projects.

It is intended that the reduced engineering control of sampling and testing procedures be permitted only for relatively small quantities of material that will not adversely affect the Traffic carrying capacity of a completed facility. Such procedures are not to be permitted in concrete for major structures, permanent mainlines, ramp pavements, or other structurally critical items.

Reduced inspection and testing frequencies are permissible <u>only</u> under the provisions outlined herein. Utilization of these Guidelines will be at the discretion of the Project Engineer <u>following consultation and approval by the Region Materials Engineer</u>. The Project Engineer will determine the feasibility of reducing any phase of engineering control on his project. His decision shall be documented in the project diary and with supplemental documentation as outlined below. Additionally, when materials are approved for test frequency reduction, the supplemental documentation shall also include a written concurrence from the RME agreeing with the decision.

SAMPLING AND TESTING OF SMALL QUANTITIES:

The materials listed below may be accepted without further sampling and testing based on visual examination, provided the source has recently furnished or is currently furnishing similar material found to be satisfactory under normal CDOT sampling and testing procedures. **Utilization of these Guidelines will be at the discretion of the Project Engineer** <u>following consultation and approval by the Region Materials Engineer</u>. *Acceptance Method:* <u>VISUAL</u>

The maximum quantities of material, which may be accepted by the above method, are:

Item 203 - Compaction:

Project Acceptance Test: 500 cubic yards or less, visually inspect and document in Project Files.

Item 206 - Structure Backfill:

50 cubic yards or less, visually inspect and document in Project Files. Central Laboratory Check Samples: 200 cubic yards or less, field test and document in Project Files.

Item 206 - Filter Material:

Project Acceptance Tests: 50 cubic yards or less, visually inspect and document in Project Files. Central Laboratory Check Samples: 200 cubic yards or less, field test and document in Project Files.

Item 206 - Bed Course Material:

Project Acceptance Tests: 100 cubic yards or less, visually inspect and document in Project Files. Central Laboratory Check Samples: 200 cubic yards or less, field test and document in Project Files.

SAMPLING AND TESTING OF SMALL QUANTITIES (CONTINUED):

Item 304 - Aggregate Base Course:

Project Acceptance Tests: Gradation, Atterberg limits and compaction 500 tons or less, visually inspect and document in Project Files.

Item 403 - Hot Mix Asphalt:

All tests, 500 tons or less, visually inspect and document in Project Files. >500 tons but <2,500 tons perform project-level test without sending samples to Central Lab.

Item 409 - Chip Seal Material:

50 tons or less, visually inspect and document in Project Files. Central Laboratory Check Sample: 200 tons or less, no sample.

Item 411 - Asphalt Materials PG Binder:

AC: 25 tons or less, no sample. Emulsion: 3,000 gallons or less, no sample. Document in Project Files.

Item 412 - Portland Cement Concrete Pavement:

Slump, air content, and compressive strength, 1,000 square yards or less combining all thicknesses, visually inspect and document in Project Files.

Item 601 - Structural Concrete:

50 cubic yards or less for all Classes of concrete, visually inspect and document in Project Files.

Item 608 - Sidewalks and Bikeways:

PCCP: 250 square yards or less combining all thicknesses of sidewalks, visually inspected and document in the Project Files.

HMA: 500 tons or less, combining all thicknesses of sidewalks, visually inspected and document in the Project Files.

Item 609 - Curb and Gutter:

500 linear feet or less for all Classes of concrete or HMA in the curbing, visually inspect and document in the Project Files.

SAMPLING AND TESTING OF LARGE QUANTITIES:

When a project has an unusually **large** quantity of any items it may be desirable to reduce the testing frequency. The following guidelines are suggested when considering test frequency reduction.

- 1. Region Materials Engineer, in cooperation with the Project Engineer, should analyze the item or items considered for reduction. The analysis should take into consideration the following:
 - The effect of reducing test frequency when analyzing a lot for the price reduction. The minimum testing frequencies are listed in the Frequency Guide Schedule for Minimum Materials Sampling, Testing, and Inspection.
 - Overall importance to the finished project should be considered because a reduction in test frequency could allow some out-of-specification material to be incorporated into the project.
 - A source being used to supply material that has a **proven record** of supplying specification material.
- 2. When the determination is made that a reduced testing frequency is warranted, the Region Materials Engineer should submit a written request to the Materials and Geotechnical Services Manager for approval. After approval has been obtained from the Materials and Geotechnical Services Manager, testing will begin using the normal frequency until good control is established. As soon as five consecutive tests indicate no deviation from specification, reduced test frequencies can begin. If a test indicates deviation from specification, normal frequency will be immediately reinstated until five consecutive tests are within specifications. It is not the intent of these guidelines to suggest that a reduction in testing frequency be made on all projects where a large quantity occurs on an item.

This should only be used in isolated cases where it would be impractical to take the normal number of tests.

OA FREQUENCY GUIDE SCHEDULE for Minimum Materials Testing, Sampling, and Inspection

{Page Intentionally Left Blank}