

REVISION OF SECTION 401
TOLERANCES FOR HOT MIX ASPHALT

Section 401 of the Standard Specifications is hereby revised for this project as follows:

In subsection 401.02(b) delete Table 401-1 and replace with the following:

**Table 401-1
TOLERANCES FOR HOT MIX ASPHALT**

Asphalt Content	± 0.3%
Asphalt Recycling Agent	± 0.2%
¹ Hot Mix Asphalt – Item 403	
² Passing the 9.5 mm (3/8 inch) and larger sieves	± 6%
² Passing the 4.75 mm (No. 4) and 2.36 mm (No. 8) sieves	± 5%
² Passing the 600 µm (No. 30) sieve	± 4%
² Passing the 75 µm (No. 200) sieve	± 2%
¹ When 100% passing is designated, there shall be no tolerance. When 90 – 100% passing is designated, 90% shall be the minimum; no tolerance shall be used.	
² These tolerances apply to the Contractor's Quality Control Testing.	