

10.0 GEOTECHNICAL, ROADWAY PAVEMENTS, AND STRUCTURE FOUNDATIONS

10.1 Design Requirements

Pavement Type (Rigid or Flexible) and Pavement Thickness shall be as identified in Table 10.1. The Contractor may further refine the Pavement Thickness as identified in Table 10.1 however the Pavement Type as identified in Table 10.1 shall not be changed. Pavement designs conducted by the Contractor shall follow the requirements set forth in the 2013 CDOT *Pavement Design Manual*, unless otherwise specified. Flexible pavements shall be designed using AASHTOWare DARWIN version 3.1 or newer. The structural layer coefficients of asphalt shall be 0.44. The asphalt binder required for flexible pavement shall be determined using LTPPBind and location-specific climate data assuming 98% reliability and slow conditions. Rigid pavement design shall follow the AASHTO *Guide for Design of Pavement Structures, 4th Edition with 1998 Supplement*. All rigid designs must pass both the faulting and corner break checks, regardless of whether it is doweled or not, using location-specific climate data.

Flexible pavements shall be designed for a 20-year design life; rigid pavements shall be designed for a 30-year design life. All pavement designs shall utilize a base year of 2016 and a Reliability of 95%. Calculated flexible pavement design thickness shall be rounded up to the nearest ½-inch. Calculated rigid pavement design thickness shall incorporate an extra ¼-inch to accommodate future grinding and then be rounded up to the nearest ½-inch.

All pavements shall be underlain by 6 inches of aggregate base course (ABC) Class 6. A structural coefficient of 0.15 and an elastic modulus of 20,000 psi shall be used to represent ABC Class 6.

Pavement designs conducted by the Contractor on local streets and facilities shall meet all the design requirements for the City and County of Denver.

The Contractor shall submit all pavement designs to CDOT for Approval with preliminary design packages.

Mechanistic empirical methodology shall not be used for design of any permanent pavement.

If the required data is not available from CDOT, the Contractor shall document and submit all traffic counts / calculations used to arrive at the Average Daily Traffic (ADT) and 18-kip Equivalent Single Axle Loads (ESAL) used. Construction of paved surfaces shall not commence until the pavement design has been reviewed and Approved by CDOT.

10.1.1 Subsurface Investigations

Geotechnical investigations conducted on Federal Boulevard, US 6, and I-25 are provided in the Reference Documents. The Contractor shall be responsible for any supplemental subsurface investigation necessary to complete the Work. Geotechnical investigations shall comply with the requirements of the 2013 CDOT *Field Materials Manual* and the 2013 CDOT *Pavement Design Manual*.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Geotechnical investigations for local roadways as defined in Section 10.1.2.5, below, shall conform to Local Agency requirements.

All supplemental investigations made by the Contractor shall be documented in a geotechnical investigation report and submitted to CDOT for Acceptance within 30 Working Days following completion of the field Work. All supplemental investigations made by the Contractor for non-CDOT roadways shall be documented in separate Geotechnical Investigation Reports according to the maintaining entity and submitted to CDOT for Acceptance.

10.1.2 Roadway Pavement Analysis and Design

Rigid pavement designs consist of Portland Cement Concrete Pavement (PCCP), with load transfer devices and tied shoulders, over 6 inches of Aggregate Base Course Class 6 (ABC Class 6) and underlain by at least 24 inches of material with an R-value greater than or equal to the minimum R-value specified in Book 2, Section 11, Table 1. Flexible pavement designs consist of two inches of Stone Matrix Asphalt (Fibers) (Asphalt) with Hot Mix Asphalt (Grading S) (100) (PG 64-22) utilized for the rest of the pavement depth over 6 inches of ABC Class 6 and underlain by a minimum of 24 inches of material with an R-value greater than or equal to the minimum R-value specified in Book 2, Section 11, Table 1. The pavement shall be uniform for all of the segments identified. All pavement shall be constructed full width, include inside and outside shoulders, if any.

Roadway and (Number of Design Lanes)	Pavement Type	Design Life (years)	Design ESAL's	Pavement Thickness (inches)
Federal Boulevard (6)	Rigid	30	5,790,899	9.5
Federal Boulevard Ramp to WB US6 (1)	Flexible	20	1,504,922	9.0
Federal Boulevard Ramp to WB US6 (2)	Flexible	20	902,953	8.5
Federal Boulevard to Braided Ramp/EB CD Road/Bryant Street (2)	Rigid	30	3,617,310	9.0
Federal Boulevard to EB US6 CD Road (1)	Rigid	30	4,231,881	9.5
WB US6 Ramp to Federal Boulevard (2)	Rigid	30	2,080,717	8.5
EB US6 Ramp to Federal Boulevard (1)	Flexible	20	1,441,789	9.0
EB US6 Ramp to Federal Boulevard (2)	Flexible	20	865,073	8.5
US6, Knox Court to Bryant Street (4)	Rigid	30	22,815,864	11.5
US6, Bryant Street to South Platte River Bridge (4)	Rigid	30	22,815,864	11.5
US6, South Platte River Bridge to I-25 (4)	Rigid	30	22,815,864	11.5
US6, I-25 to BNSF (4)	Rigid	30	11,377,017	11.0

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

EB US6 CD Road (3)	Rigid	30	12,604,816	10.5
Braided Ramp from Federal Boulevard to EB US6 (1)	Rigid	30	1,797,948	8.0
Federal Boulevard Ramp to Bryant Street (1)	Rigid	30	740,258	7.0
WB US6 CD Road (2)	Rigid	30	6,611,077	10.0
Bryant Street Ramp to Federal Boulevard (1)	Rigid	30	1,091,517	7.5
5 th Avenue / Decatur Street (1 per direction)	Flexible	20	700,000	8.5
Residential Side Streets (1 per direction)	Flexible	5	411,458	8.0
SB I-25 Ramp to WB US6 (2)	Flexible	20	7,432,161	12.0
	Rigid	30	17,977,261	11.5
NB I-25 Ramp to WB US6 (1) Note: Also referred to as I-25 CD Road	Flexible	20	9,772,243	13.0
	Rigid	30	22,936,118	11.5
NB I-25 Ramp to EB US6 (1)	Flexible	20	1,854,019	10.0
	Rigid	30	5,346,497	9.5
SB I-25 Ramp to EB US6 (1)	Flexible	20	3,449,904	10.5
	Rigid	30	8,455,409	10.0
I-25 (NB and SB) (8)	Flexible	20	30,426,404	15.5

PCCP on Federal Boulevard shall extend to the end of the curb return on intersection side streets. All PCCP shall be doweled and tied per CDOT M-412 unless otherwise specified by CDOT. The Contractor shall prepare a pavement jointing plan per CDOT M-412, the 2013 Pavement Design Manual, and industry best practices. The jointing plan shall be submitted to CDOT for approval with the preliminary design documents.

The top 2 inches of all flexible pavement alternatives shall be Stone Matrix Asphalt (Fibers) (Asphalt). The nominal maximum aggregate size of the SMA shall be ½ inch. All references to SMA shall be taken to be Stone Matrix Asphalt (Fibers)(Asphalt) or SMA (Fibers)(Asphalt). Stone Matrix Asphalt (Fibers) (Asphalt) shall not contain any reclaimed asphalt pavement. The intermediate and bottom lifts of asphalt shall be HMA (Grading S) (100) (PG 64-22). The lift breakdown of the intermediate and bottom lifts shall follow the guidelines established in Table 3.7 of the 2013 CDOT Pavement Design Guide. The thickness of each overlying lift shall be equal to or less than the thickness of the lift directly below. Any flexible pavement alternative offered by the contractor shall indicate the type of asphalt and thickness of all lifts that comprise the pavement section.

In addition to the pavements shown in the above table, the Contractor shall conduct a mill and overlay operation on 6th Avenue full width from US6 Milepost 282.3 to the west limit of the Federal Boulevard Bridge and Roadway Segment as identified on Book 2, Section 2, Exhibit B. The milling depth shall be 2 inches. The overlay depth shall be 2 inches using SMA (Fibers) (Asphalt) and shall match the existing cross slope of the overlay.

The Contractor shall submit pavement designs for all detour pavements for CDOT Acceptance. Detour pavements shall utilize at a minimum grading, gyrations, and binder equivalent to Hot Mix Asphalt (Grading S) (100) (PG 64-22). Where detour pavement abuts existing pavement which has a base of aggregate base course, the detour must include a layer of aggregate base

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

course which shall serve to convey potential underpavement drainage away from the permanent pavement. The Contractor shall be responsible for maintenance of all detour pavements.

10.1.2.4 Alternate Pavement Designs

Intentionally left blank.

10.1.2.5 Non-CDOT Roadways Pavement Designs

The following local roadway Pavement designs and sections shall conform to Local Agency requirements:

1. 5th Avenue, Canosa Court, Alcott Street, Bryant Street, and other affected roadways maintained by the City and County of Denver. City and County of Denver recognizes the Metropolitan Government Pavement Engineers Council (MGPEC) Pavement Design Standards and Construction Specifications for roadway pavement design and construction.

10.1.3 Structure Foundation Analysis and Design

Intentionally left blank.

10.2 Construction Requirements

The Contractor shall construct the PCCP, SMA, HMA, and all other paved surfaces in accordance with the requirements of the Contract Documents. Construction of Contractor-designed permanent paved surfaces shall not commence until the pavement design has been Approved by CDOT.

Where it is required to cut existing pavement, the cutting shall be done to a neat work line full depth with a pavement-cutting saw or other method as approved by the CDOT.

At no time should the blunt end of guardrail, barrier, end treatment, etc. be exposed to oncoming traffic.

The Contractor shall be responsible for constructing Safety Edge as specified in Book 2, Section 13.3.6.

To provide for adequate sulfate resistance in all concrete supplied, Severity of Potential Exposure shall be Class 2 for this Project. The Contractor may, at their expense, have a certified laboratory test the subgrade as per the CDOT *Field Materials Manual*. Testing shall be at the same schedule and frequency as required for a preliminary soil survey. The Contractor may propose a different Class of Exposure for the Project based on the test results.

Any curb and gutter, which is to remain and is damaged as a result of the contractor's operation, shall be replaced at the contractor's expense.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

10.2.1 Roadway Pavement Construction Requirements

A minimum of two weeks prior to the proposed use of any pavement on the Project, a Pre-paving Conference shall be conducted. At the Pre-paving Conference, the Contractor shall present to CDOT for Approval mix designs for SMA, HMA, and PCCP, as well as final jointing plans for PCCP.

10.2.2 Roadway Pavement Types and Thickness Requirements

10.2.2.1 Full-Depth Asphalt Pavement

A tack coat is required between layers of bituminous pavement. Diluted emulsified asphalt for tack coat shall consist of 1 part emulsified asphalt and 1 part water. Rates of application shall be 0.10 Gal / Sq. Yd. (Diluted) or as determined by the CDOT at the time of application. Any layer of bituminous pavement that is to have a succeeding layer placed thereon shall be completed full-width before a succeeding layer is placed.

10.2.2.2 Stone Matrix Asphalt Pavement

Stone Matrix Asphalt Pavement (SMA) Acceptance shall be based on gradation.

Full-width SMA shall be utilized as the top lift of all proposed flexible pavement and on structures, deck rehabilitations, unless otherwise Approved by CDOT. SMA shall utilize PG 76-28 asphalt binder grade.

10.2.2.3 Hot Mix Asphalt Pavement

HMA mixes shall be subject to voids acceptance.

10.2.2.4 Asphalt Overlay

Locations with ruts shall be milled to a depth of ½” below the bottom of the ruts.

10.2.2.5 Asphalt Patching

Patching of permanent pavement shall be to the depth of the surrounding existing / proposed pavement as directed by CDOT. The top lift must match the depth of the 1st lift of the proposed pavement and conform to the requirements of SMA (Fibers) (Asphalt) .Lower lifts shall conform to the requirements of HMA (Grading S) (100) (PG 64-22). The minimum and maximum lift thicknesses shall be 2 and 3 inches, respectively, for SMA (Fibers) (Asphalt) and 2.25 and 3.5 inches, respectively, for HMA (Grading S) (100) (PG 64-22). The thickness of each lift shall be less than or equal to the thickness of lift directly beneath it. All patching shall be per CDOT.

10.2.2.6 Portland Cement Concrete Pavement

Portland Cement Concrete pavement shall meet compressive strength requirements as identified in the most current CDOT Standard Specifications for Roadway and Bridge Construction. The Contractor shall be responsible for PCCP joint design. The Contractor's joint

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

design shall include tied inside and outside shoulders. Outside mainline US 6 shoulders shall include transverse load transfer devices (DC joints). PCCP joint design shall comply with the requirements of Book 3, including but not limited to the CDOT *M & S Standard Plans*, and the CDOT *Pavement Design Manual*. The PCCP longitudinal and transverse joint designs shall be compatible with lane and shoulder configurations. The Contractor shall submit the pavement joint design to CDOT for Acceptance along with the preliminary design documents. PCCP construction shall not commence until the PCCP Jointing Plan is Accepted.

The Contractor shall fine mainline US 6 outside shoulders per CDOT standards. Station stamping is not required.

10.2.2.6 Pavement Smoothness

The Contractor shall construct the PCCP/flexible pavement for the Project to the smoothness requirements as set forth in Table 10.2.

Location	Pavement Smoothness Category⁽ⁱⁱ⁾
Flexible Pavement	HRI Category II (Inches/mile)
Rigid Pavement	HRI Category II (Inches/mile)
Overlay	HRI Category I (Inches/mile)
Proposed Structure	HRI Category II (Inches/mile)

10.3 Project Special Provisions

The following specifications modify and take precedence over the Standard Specifications.

10.3.1 Removal of Asphalt Mat (Planing)

Section 202 of the Standard Specifications is hereby revised for this project as follows:

Delete subsection 202.09, and replace it with the following:

202.09 Removal of Asphalt Mat (Planing). Prior to beginning planing operations, the Contractor shall submit a planing plan and a Quality Control Plan (QCP) for approval by the Engineer. The planing plan shall include at a minimum:

- (1) The number, types and sizes of planers to be used.
- (2) The width and location of each planing pass.
- (3) The number and types of brooms to be used and their locations with respect to the planers.
- (4) The proposed method for planing and wedging around existing structures such as manholes, valve boxes, and inlets.
- (5) The longitudinal and transverse typical sections for tie-ins at the end of the day.
- (6) If requested by the Engineer, a plan sheet showing the milling passes.

The QCP shall include as a minimum:

- (1) The schedule for replacing the cutting teeth.
- (2) The daily preventive maintenance schedule and checklist.
- (3) Proposed use of automatic grade controls.
- (4) The surface testing schedule for smoothness.
- (5) The process for filling distressed areas.
- (6) The schedule for testing macrotexture of the milled surface.
- (7) Corrective procedures if the milled surface does not meet the minimum macrotexture specification.
- (8) Corrective procedures if the milled surface does not meet the minimum transverse or longitudinal surface finish when measured with a 10 foot straightedge.

The Contractor shall not start the planing operation until the hot mix asphalt (HMA) mix design has been approved and a Form 43 has been signed by the Engineer.

The existing pavement shall be milled to the cross-slope as shown on the plans, and shall have a surface finish that does not vary longitudinally or transversely more than 3/8 inch from a 10 foot straightedge. A 10 foot straightedge shall be supplied by the Contractor.

All milled surfaces shall be broomed with a pick-up broom, unless otherwise specified, before being opened to traffic. A sufficient number of brooms shall be used immediately after planing to remove all milled material remaining in the roadway.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

If the Contractor fails to adequately clean the roadway, work shall cease until the Engineer has approved the Contractor's revised written proposal to adequately clean the roadway.

The milled surface shall have a macrotexture equal to or less than 0.170 inches for single-lift overlays and 0.215 inches for multiple-lift overlays as tested in accordance with CP 77. Milled surfaces that do not meet these criteria shall require corrective action in accordance with the QCP. The Contractor shall be responsible for testing the macrotexture of the milled surface at the location directed by the Engineer in accordance with CP 77 at a stratified random frequency of one test per 10,000 square yards or a minimum of once per work day.

At the completion of each day's work, longitudinal vertical edges greater than 1 inch shall be tapered. No transverse vertical edges will be allowed. Longitudinal milled surface tie-ins to existing pavement shall be tapered to not less than a 3:1 slope, transverse milled surface tie-ins to existing pavement shall be tapered to not less than a 50:1 slope. Transverse tapered joints may be tapered with the planing machine, a temporary asphalt ramp, or other methods approved by the Engineer. No longitudinal joint between the milled and existing surfaces shall fall between 1 to 5 feet of any lane line.

If the transverse joint is tapered with a temporary asphalt ramp, the milled surface at the joint shall be constructed as a butt joint the full depth of the lift of asphalt to be placed on the milled surface. The Contractor shall be responsible for maintaining this asphalt ramp until all corresponding HMA is placed. All work associated with this joint will not be paid for separately, but shall be included in the cost of planing.

If the transverse joint is tapered with a planing machine, a butt joint shall be cut into the taper the full depth of the lift of asphalt to be placed on the milled surface prior to commencement of resurfacing. All work associated with this joint will not be paid for separately, but shall be included in the cost of planing.

Other approved transverse joint tapers shall be maintained at the expense of the Contractor, and at a minimum shall incorporate a butt joint the full depth of the lift of asphalt to be placed on the milled surface prior to commencement of resurfacing.

Distressed or irregular areas identified in the planed surface by the Engineer shall be patched.

The roadway shall be left in a safe and usable condition at the end of each work day. The Contractor shall take appropriate measures to ensure that the milled surface does not trap or hold water. All required pavement markings removed by the planing shall be restored before the roadway is opened to traffic.

All milled surfaces to be overlaid with HMA shall be covered with new asphalt within 7 working days. All areas on this project that are not overlaid within the specified working days will be assessed a lane rental fee of \$500 per occurrence for each day or fraction thereof and any required surface repairs shall be paid for by the Contractor.

All planing shall be completed full width and parallel to the travel lanes before resurfacing commences unless otherwise directed by the Engineer.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

All material generated by the planing operation shall become the property of the Contractor unless otherwise noted in the Contract.

Add subsection 202.091 immediately following subsection 202.09 as follows:

202.091 Equipment

Each planer shall conform to the following:

The planer shall have sufficient power, traction and stability to maintain an accurate depth of cut. The propulsion and guidance system of the planer shall be maintained in such condition that the planer may be operated to straight and true lines.

The planer shall be capable of operating with automatic grade controls (contact or non-contact) on both sides of the machine using a 30 foot averaging system or other approved grade control systems. The use of such controls shall be described in the Contractor's QCP.

The planer shall be capable of picking up the removed material in a single operation. A self-loading conveyor shall be an integral part of the planer. Windrows will not be allowed.

Subsection 202.12 shall include the following:

Macrotexture testing, macrotexture corrective actions, planers, brooms and all other work necessary to complete the item will not be measured and paid for separately, but shall be included in the work.

10.3.2 Plant Mix Pavement Compaction (Pneumatic Tire Rollers)

Section 401 of the Standard Specifications is hereby revised for this Project as follows:

In Subsection 401.17, first paragraph, delete the second sentence and replace with the following:

Both steel wheel and pneumatic tire rollers shall be required on this Project. If the Contractor can demonstrate to CDOT that all of the manufacturer's recommendations were followed and the pneumatic tire roller is detrimental to the finished surface of the HMA, the Contractor may request CDOT to waive the pneumatic tire roller requirement. Pneumatic tire rollers shall not be used on SMA pavement. Steel wheel rollers shall not be used in vibratory mode when compacting SMA on bridge decks.

10.3.3 Conformity to the Contract of Hot Mix Asphalt

Section 106 of the Standard Special Provisions is hereby revised for this Project as follows:

Subsection 106.05 shall include the following:

For this Project, Contractor process control testing of HMA is mandatory.

10.3.4 Aggregate Base Course Class 6

Section 304 of the Standard Specifications is hereby revised for this Project as follows:

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Subsection 304.02 shall include the following:

Materials for the base course shall be ABC Class 6 as shown in Subsection 703.03.

The ABC Class 6 must meet the gradation requirements and have a resistance value of at least 78 when tested by the Hveem Stabilometer method. Test result documentation for ABC Class 6 used for this project must be provided prior to use on site.

10.3.5 Aggregate Base Course Class 6 Special

Section 304 of the Standard Specifications is hereby revised for this Project as follows:

Subsection 304.02 shall include the following:

Recycled Asphalt Pavement (RAP), the product of rotomill tailings or crushed asphalt pavement, utilized as ABC Class 6 (Special), shall be of uniform quality. The RAP shall meet the gradation requirements for ABC Class 6. The material shall not contain clay balls, vegetable matter, or other deleterious substances. RAP is not required to meet the requirements of Subsection 703.03.

Subsection 304.04 shall include the following:

The maximum density of RAP shall be determined in accordance with AASHTO T-180, Method A. The field moisture determination for correction to dry density shall be determined by oven or microwave drying. Moisture determination of RAP using a nuclear gauge will not be permitted.

10.3.6 Hot Mix Asphalt

Section 403 of the Standard Specifications is hereby revised for this Project as follows:

Subsection 403.02 shall include the following:

The design mix for HMA shall conform to the following:

Table 403-1

Property	Test Method	Value For Grading			
		S (100)			Patching
Air Voids, percent at: N (initial) [for information only] N (design)	CPL 5115	3.5 – 4.5			3.5 – 4.5
Lab Compaction (Revolutions): N (initial) [for information only] N (design)	CPL 5115	8 100			8 100
Stability, minimum	CPL 5106	30			30

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Table 403-1

Property	Test Method	Value For Grading			
Aggregate Retained on the 4.75 mm (No. 4) Sieve with at least 2 Mechanically Induced fractured faces, % minimum	CP 45	70			70
Accelerated Moisture Susceptibility Tensile Strength Ratio (Lottman), minimum	CPL 5109 Method B	80			80
Minimum Dry Split Tensile Strength, kPa (psi)	CPL 5109 Method B	205 (30)			205 (30)
Grade of Asphalt Cement, Top Layer					PG 76-28
Grade of Asphalt Cement, Layers below Top		PG 64-22			PG 64-22
Voids in the Mineral Aggregate (VMA) % minimum	CP 48	See Table 403-2			See Table 403-2
Voids Filled with Asphalt (VFA), %	AI MS-2	65-75			65-75
Dust to Asphalt Ratio Fine Gradation Coarse Gradation	CP 50	0.6 – 1.2 0.8 – 1.6			0.6 – 1.2 0.8 – 1.6

Notes:

- AI MS-2 = Asphalt Institute Manual Series 2.
- The current version of CPL 5115 is available from CDOT.
- Mixes with gradations having less than 40% passing the 4.75 mm (No. 4) sieve shall be approached with caution because of constructability problems.
- Gradations for mixes with a nominal maximum aggregate size of one-inch or larger are considered a coarse gradation if they pass below the maximum density line at the #4 screen.
Gradations for mixes with a nominal maximum aggregate size of ¾ inch or smaller are considered a coarse gradation if they pass below the maximum density line at the #8 screen.

All mix designs shall be run with a gyratory compaction angle of 1.25 degrees and properties must satisfy Table 403-1. Form 43 will establish construction targets for Asphalt Cement and all mix properties at Air Voids up to 1.0% below the mix design optimum.

Table 403-2			
Minimum Voids in the Mineral Aggregate (VMA)			
Nominal Maximum Size*, mm (inches)	***Design Air Voids **		
	3.5%	4.0%	4.5%
37.5 (1½)	11.6	11.7	11.8
25.0 (1)	12.6	12.7	12.8
19.0 (¾)	13.6	13.7	13.8
12.5 (½)	14.6	14.7	14.8
9.5 (¾)	15.6	15.7	15.8
<p>* The Nominal Maximum Size is defined as one sieve larger than the first sieve to retain more than 10%.</p> <p>** Interpolate specified VMA values for design air voids between those listed.</p> <p>*** Extrapolate specified VMA values for production air voids beyond those listed.</p>			

As a part of the Contractor’s Quality Management Plan, the Contractor shall outline the steps taken to minimize segregation of HMA. The Quality Management Plan shall define a process by which the Contractor shall address unacceptable segregation, but, at a minimum, the paving shall stop and the cause of segregation shall be corrected before paving operations will be allowed to resume.

HMA for patching shall conform to the gradation requirements for SMA for the top lift and HMA (Grading S) (100) (PG 64-22) for intermediate and lower lifts. All patching determinations shall be the responsibility of the Contractor with consultation with CDOT.

A minimum of 1% hydrated lime by weight of the combined aggregate shall be added to the aggregate for all HMA.

Subsection 403.03 shall include the following:

If liquid anti-stripping additive is added at the plant, an approved in-line blender must be used. The blender shall be in the line from the storage tank to the drier drum or pugmill. The blender shall apply sufficient mixing action to thoroughly mix the asphalt cement and anti-stripping additive.

The Contractor shall construct the Work such that all roadway pavement placed prior to the time paving operations end for the year, shall be completed to the full thickness required by the plans. The Contractor’s progress schedule shall show the methods to be used to comply with this requirement.

10.3.7 Stone Matrix Asphalt Pavement

Sections 401 and 703 of the Standard Specifications are hereby revised for this Project as follows:

Subsection 401.02 shall include the following:

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Recycled Asphalt Pavement (RAP) shall not be used in Stone Matrix Asphalt (SMA) mix.

Subsection 401.09 shall include the following:

Each SMA load shall be completely covered and securely fastened with a full tarp.

Subsection 401.16 shall include the following:

The SMA mixture shall be transported and placed on the roadway without drain-down or flushing. All flushed areas behind the paver shall be removed immediately upon discovery. If more than 50 square feet of flushed SMA pavement is ordered removed and replaced in any continuous 500 linear feet of paver width laydown, operations shall be discontinued until the source of the flushing has been found and corrected. The Engineer shall designate the depth and area of all flushed areas requiring removal and replacement. All costs associated with the removal and replacement of the flushed areas shall be at the Contractor's expense.

Subsection 401.17 shall include the following:

Rollers shall not be used in a vibratory mode on SMA unless they are first used successfully in the demonstration control strip specified in subsection 403.03. Pneumatic wheel rollers shall not be used on SMA mix.

Stone Matrix Asphalt Pavement shall be placed and compacted in accordance with the temperatures listed in subsection 401.07 as revised for this Project.

The relative compaction for all SMA mixtures will be measured from roadway cores in accordance with CP 44, Method B, unless the SMA mixture is being placed on a structure (bridge deck) in which case nuclear gauge measurements may be used.

When cores are used, the Contractor shall provide all labor and equipment for the coring operation and filling the core holes. When nuclear density gauges are used, the tests will be performed in accordance with CP 81 and CP 82.

In-place density for SMA not placed on a bridge shall be 93 to 97% of the SMA mix maximum specific gravity as measured according to CP 51.

At a minimum frequency of once per day, the in-place density for SMA placed on the bridge deck shall be measured according to CP 81. The in-place density of SMA shall be a minimum of 94 percent of the SMA mix maximum specific gravity as measured according to CP 51.

Subsection 401.22 shall include the following:

Acceptance, testing, and pay factors for SMA shall be in accordance with subsections 105.05 and 106.05 as revised for this Project for HMA. The specifications for gradation acceptance shall be applied for all SMA placed on the project.

Subsection 703.06 shall include the following:

Mineral filler for the Stone Matrix Asphalt pavement shall be limestone dust and shall meet the requirements of this subsection and the following:

Plasticity Index (AASHTO T90) 4% Maximum

The Contractor shall submit hydrometer analysis (AASHTO T88) for the mineral filler used in the SMA mix.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Section 403 of the Standard Specifications is hereby revised for this Project as follows:

Subsection 403.01 shall include the following:

This work includes placing a Stone Matrix Asphalt (SMA) pavement as shown on the plans.

Subsection 403.02 shall include the following:

The SMA gradation for this Project shall be ½ inch.

Mixture design and field control testing of SMA shall be performed using either the SuperPave (CPL 5115, 100 Gyration) or the Marshall Method (AASHTO T245, 50 Blow).

The Contractor shall submit a mix design meeting the appropriate specification requirements for the following to CDOT at the Pre-paving Conference:

The SuperPave SMA mix design shall conform to the requirements of Table 403-1a:

Table 403-1a		
Property	Test Method	Value for SMA
Air Voids, percent at: N(Design)	CPL 5115	3.0 – 4.0
Lab compaction (Revolutions) N(Design)	CPL 5115	100
Accelerated Moisture Susceptibility, tensile strength Ratio, (Lottman), minimum	CPL 5109, Method B	70
Minimum Dry Split Tensile Strength, psi	CPL 5109, Method B	30
Grade of Asphalt Cement		PG 76-28
Voids in the Mineral Aggregate (VMA) %, minimum	CP 48	17
Draindown at Production Temperature	AASHTO T305	0.3 maximum
% VCA ¹ _{MIX}	AASHTO R 46	Less than VCA _{DRC} ²
Note: The current version of CPL 5115 is available from CDOT		
Note: Copies of AASHTO R 46 and M 325 can be obtained from CDOT		
Note: ¹ Voids in the Coarse Aggregate		
Note: ² Dry-rodded condition		

Form 43 will establish construction targets for asphalt cement and all mix properties at air voids up to 1.0% below the mix design optimum.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

The Marshall SMA mix design shall conform to the following:

Mix Properties	Value
Stability, Marshall Compactor	1400 lbs., min
% Voids in Total Mix	3 – 4%
VMA (% Voids in the Mineral Aggregate)	17 min.
Lottman, CPL 5109, Method B	70% min
Dry Tensile Strength, (CPL 5109)	30 psi, min.

Regardless of mix design method, a minimum of 1% hydrated lime by weight of the combined aggregate shall be added to the aggregate for all Stone Matrix Asphalt.

The SMA mix design must be Approved by CDOT before any pavement is placed on the project. In addition, the Contractor shall provide field control testing during production of the SMA mix and for the demonstration control strip. The Contractor shall perform the following tests and provide the results to CDOT during production:

If a Superpave SMA mix design is used, the Contractor shall perform the following tests and provide the results to the Engineer during production:

Superpave Mix Property	Frequency
Draindown (AASHTO T 305)	1/1000 tons or fraction thereof
Percent Voids in the total mix @ $N_{(design)}$	1/1000 tons or fraction thereof
VMA (Percent Voids in the Mineral Aggregate) @ $N_{(design)}$	1/1000 tons or fraction thereof
Lottman, CPL 5109, Method B	1/5000 tons or fraction thereof
Dry Tensile Strength, CPL 5109	1/5000 tons or fraction thereof
Percent AC & Aggregate Gradation CP 5120	1/1000 tons or fraction thereof

If a Marshall SMA mix design is used, the Contractor shall perform the following tests and provide the results to the Engineer during production:

Marshall Mix Property	Frequency
Draindown (AASHTO T 305)	1/1000 tons or fraction thereof
Stability (Marshall)	1/1000 tons or fraction thereof
Percent Voids in the total mix	1/1000 tons or fraction thereof
VMA (Percent Voids in the Mineral Aggregate)	1/1000 tons or fraction thereof
Lottman, CPL 5109, Method B	1/5000 tons or fraction thereof
Dry Tensile Strength, CPL 5109	1/5000 tons or fraction thereof
Percent AC & Aggregate Gradation CP 5120	1/1000 tons or fraction thereof

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

Subsection 403.03 shall include the following:

The mineral filler for SMA shall be stored in a separate silo and added automatically in the correct proportion. The mineral filler addition equipment shall be electronically or mechanically interlocked to the aggregate feed sensors so that the proper amount of mineral filler is added whenever SMA is produced.

The SMA mineral filler shall be added at the same point the asphalt cement is added to the aggregate.

Tack coat between the existing pavement and Stone Matrix Asphalt pavement shall be placed at a rate between 0.03 and 0.05 gallons per square yard.

Before proceeding with SMA placement, the Contractor shall demonstrate the ability to produce and place a satisfactory mix in a Demonstration Control Strip (DCS). The Contractor will coordinate with the Quality Control Manager on the proposed location of the DCS. The DCS shall consist of a minimum quantity of 500 tons placed in one lane, full width. Within the last 200 tons of SMA placed in the DCS, the Contractor and CDOT shall determine properties (VMA, Voids, in-place density, AC content, gradation, and Marshall Stability, if required) of the project produced SMA mix used in the DCS and provide the results to the Contractor's Quality Control Manager. The Contractor may proceed with full production if all mixture properties are within the specified tolerances and the project compaction is established and approved by CDOT.

If a DCS will be placed on the actual roadway, it shall be full width and shall extend for a minimum distance of 150 feet. The location of the DCS shall be no closer than 100 feet to the expansion joint of any bridge with concurrent deck rehabilitation or construction.

To determine the in-place density and roller pattern, one core shall be taken at three random locations within the last 200 tons of the DCS. As part of the Contractor's QMP, the coring locations shall be determined using a stratified random sampling process. The cores shall be immediately submitted to the Contractor's Quality Manager and will be used for determining acceptance of the DCS. Densities of the random samples will be determined by cores according to CP 44. Coring shall be performed by the Contractor under the Quality Manager's observation.

The DCS will be designated as a separate process.

Subsection 403.04 shall include the following:

Stone Matrix Asphalt will be measured by the actual number of tons that are completed and accepted.

Subsection 403.05 shall include the following:

Mix design, furnishing, hauling, preparing, and placing all materials, including aggregates, asphalt cement, limestone dust, hydrated lime, tack coat, and approved demonstration control strip; labor, equipment tools, setting of lines and guides where specified, and all other work necessary to complete the item will not be paid for separately but shall be included in the work.

Stone Matrix Asphalt will be measured by the actual number of tons that are completed and accepted.

REQUEST FOR PROPOSAL – US6 BRIDGES DESIGN BUILD PROJECT

BR 0061-083, SUB ACCOUNT 18838 (CN)

BOOK 2 – TECHNICAL REQUIREMENTS

SECTION 10 – GEOTECHNICAL

10.3.8 Detour

Section 621 is hereby added to the Standard Specifications for this Project and shall include the following:

621.01 This work consists of constructing detours as shown in the plans for all phases of construction on US 6 and all applicable side streets; maintenance of the detours; removal of the detours; and removal and replacement of appurtenances required to construct and operate the detours including but not limited to guardrail, curb and gutter, detour pavement, embankment material and unclassified excavations.

621.02 All materials required for detour shall comply with project standard specifications and special provisions.

The Contractor shall be responsible for quality control required to assure adequate quality of embankment material, aggregate base course, HMA used in the construction of the detour.

621.03 The detour locations and dimensions for all phases of construction shall be as shown on the plans.

If the materials and thickness furnished for the detour pavement result in an inadequate detour structure, the Contractor will provide additional thickness, materials, or other measures necessary to provide a satisfactory pavement for the life of the detour. These additional improvements shall be furnished at no additional cost. All necessary signs, pavement markings and other traffic control devices shall be provided in accordance with the traffic control plan.

621.04 The Contractor shall maintain the detour for the entire period that it is open to traffic. Any distress that affects the ride, safety, or serviceability of the detour roadway shall be corrected to the satisfaction of the CDOT at the expense of the Contractor.

The Contractor shall have a maintenance plan for all hours of the day (7 days a week) for executing a long term patch of damaged detour pavement, and have forces available to perform this work within 2 hours of notice of such damage. The Contractor shall designate a person to be "on call" during all non-working hours, including no work periods as a point of contact for this work.

If CDOT determines the detour has deteriorated to the point where the safety of the traveling public is compromised (i.e. potholes), the lane(s) in question shall be closed and the Contractor shall be directed to execute their maintenance plan. If the Contractor is unresponsive to this order by CDOT, CDOT maintenance forces will be mobilized to close the lane and maintain the closure until such time as the Contractor is available to perform this work. CDOT Maintenance forces will be responsible for the lane closure only, and only until such time as the Contractor arrives on site and relieves them. CDOT Maintenance will not be responsible for repair of any of the contract installed detour. All time and expense for CDOT Maintenance work will be tracked by CDOT and deducted from money due to the Contractor. Any lane closures that are required outside of the allowable lane closure hours will be charged as 'working time violation' as established in this contract.

10.4 Deliverables

At a minimum, the Contractor shall submit the following to CDOT for review, Approval, and/or Acceptance:

Deliverable	Review, Acceptance, or Approval	Schedule
Supplemental Geotechnical Investigation Report	Acceptance	Within 30 Working Days following completion of field work
Pavement Design Report	Approval	Submitted with Design Packages
Paving Quality Control Plan	Approval	Prior to beginning paving operations
SMA Mix Design	Approval	At the Pre-paving Conference and at least 14 Days prior to the use of any SMA pavement on the Project
HMA Mix Designs	Approval	At the Pre-paving Conference and at least 14 Days prior to the use of any HMA pavement on the Project
Detour Pavement Design	Acceptance	At the Pre-paving Conference and at least 14 Days prior to the use of any Detour Pavement on the Project
PCCP Jointing Plan	Acceptance	Submitted with Design Packages
PCCP Mix Designs	Approval	At the Pre-paving Conference and at least 14 Days prior to the use of any PCCP on the Project

All deliverables shall also conform to the requirements of Book 2, Section 3, Quality Management.